TECAPEEK CMF white - Stock Shapes (rods, plates, tubes)

Chemical Designation
PEEK (Polyetheretherketone)

Colour
white

Density
1.63 g/cm^3

Fillers
ceramic

Main features
- high dimensional stability
- good machinability
- high strength
- high stiffness
- low thermal expansion
- low burring
- good heat deflection temperature
- very good thermal stability

Target Industries
- electrical engineering
- precision engineering
- semiconductor technology
- vacuum technology

Mechanical properties	condition	value	unit	test method		comment
Modulus of elasticity (tensile test)	@ 73 °F	1,227,111	psi	ASTM D 638	1)	(1) All properties derived from machined plate test specimens (2) Data obtained from public source (3) Data obtained from public source
Tensile strength at yield	@ 73 °F	14,122	psi	ASTM D 638		
Tensile strength at break	50 mm/min	15,200	psi	DIN EN ISO 527-2	2)	
Elongation at yield (tensile test)	50 mm/min	3	%	DIN EN ISO 527-1	3)	
Elongation at break (tensile test)	@ 73 °F	4.85	%	ASTM D 638		
Flexural strength	@ 73 °F	23,642	psi	ASTM D 790		
Modulus of elasticity (flexural test)	@ 73 °F	783,585	psi	ASTM D 790		
Compression strength	@ 73 °F @ 1% strain	1,855	psi	ASTM D 695		
Compression strength	@ 73 °F @ 10% strain	20,712	psi	ASTM D 695		
Compression modulus	@ 73 °F	335,369	psi	ASTM D 695		
Impact strength (Izod)	@ 73 °F notched	0.66	ft-lbs/in	ASTM D 256		
Impact strength (Izod)	@ 73 °F unnotched	15.23	ft-lbs/in	ASTM D 256		
Rockwell hardness	M-Scale	102		ASTM D 785		
Coefficient of friction	dynamic	0.214		ASTM D 1894		
Coefficient of friction	static	0.174		ASTM D 1894		

Thermal properties	condition	value	unit	test method		comment
Melting temperature		643	°F	-	1)	(1) ASTM D3418 (2) Data obtained from public source
Service temperature	Long Term	500	°F	-	2)	
Service temperature	short term	500	°F	-		
Thermal expansion (CLTE)	73 F to 140 F	2.23	*10^{-5} in/in/°F	ASTM E 831		
Thermal expansion (CLTE)	73 F to 212 F	2.27	*10^{-5} in/in/°F	ASTM E 831		
Thermal expansion (CLTE)	212 F to 302 F	2.58	*10^{-5} in/in/°F	ASTM E 831		
Thermal conductivity		2.60	BTU-in/hr-ft^2-°F	ASTM E1530		

Electrical properties	condition	value	unit	test method	comment
surface resistivity		5.2E+15	Ω/square	ASTM D 257	
volume resistance		3.5E+15	Ω*cm	ASTM D 257	
Dielectric strength	S/T, in oil	168	V/mil	ASTM D 149	
Dissipation factor	1 MHz dry	0.0032		ASTM D 150	
Dielectric constant	1 MHz dry	4.1		ASTM D 150	

Other properties	condition	value	unit	test method		comment
Moisture absorption	@ 24 hrs	0.03	%	ASTM D 570		(1) Data obtained from public source
Flammability (UL94)		V0		-	1)	

- TECAPEEK products are based on Victrex® PEEK polymer.

Information about products and services sold by Ensinger, including without limitation information contained in this document do not constitute a warranty by Ensinger as to the quality and state or durability of products or services, or any guarantee of chemical resistance. Such information reflects the current state of our knowledge and is intended only to assist and advise the recipient. The recipient shall not be entitled to rely on Ensinger provided information and the recipient agrees to evaluate such information, to make an independent decision regarding the suitability of such information, products and services for its application, and only use such products, services and information pursuant to then current good product stewardship principles and all regulatory requirements applicable to the recipient's business. Values are guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. Data sheet values are subject to periodic review and the most recent update can be found at www.ensingerplastics.com

Ensinger Inc. Headquarters 365 Meadowlands Boulevard Washington, PA 15301, USA
Phone 800-243-3221 Sales Phone 800-869-4029
Technical Fax 724-746-9209
sales@ensingerusa.com

Date: 2025/07/16
Version: A4