PEEK-SGRN201G
Polyetheretherketone (PEEK)

TECHNICAL DATA SHEET

Description

Sciengy® PEEK-SGRN201G is a medium viscosity type, standard flow, unreinforced PolyEtherEtherKetone (PEEK), granules for injection molding and extrusion.

Unfilled, Standard

Series	Unreinforced
ISO Designation	>Unfilled PEEK<
Process Method	Injection molding, Film Extrusion

Properties

Physical	**Value**	**Units**	**Test Standard**
Density	1.30	g/cm³	ISO 1183
Mold Shrinkage (Machine Direction)	1.00	%	GB/T 15585
Mold Shrinkage (Transverse Direction)	1.20	%	GB/T 15585
Water Absorption (24h @23°C)	0.07	%	ISO 62
Mechanical	**Value**	**Units**	**Test Standard**
Tensile Stress at Break (5 mm/min)	98	MPa	ISO 527
Tensile Modulus at Break (1 mm/min)	3.7	GPa	ISO 527
Elongation at Break (23℃)	25	%	ISO 527
Flexural Modulus at Break (23℃)	3.9	GPa	ISO 178
Flexural Strength at Break (23℃)	165	MPa	ISO 178
Notched Izod Impact Strength @23℃ (V-notched)	7.0	kJ/m²	ISO 180
Thermal	**Value**	**Units**	**Test Standard**
Melting Temperature (10°C/min)	343	°C	ISO 11357
Heat Deflection Temp. High Load (1.8 MPa)	152	°C	ISO 75
Glass Transition (Tg)	150	°C	ISO 11357
Melt Flow Rate (380℃, 5kg)	25	g/10min	ISO 1133
Thermal expansion coefficient (T<Tg)	60	ppm/℃	ISO 11359
Thermal expansion coefficient (T>Tg)	140	ppm/℃	ISO 11359
Thermal conductivity (23℃)	0.29	W/mk	ISO 22007-4
Electrical Properties	**Value**	**Units**	**Test Standard**

PEEK-SGRN201G
Polyetheretherketone (PEEK)

TECHNICAL DATA SHEET

Dielectric Strength (60*60*1mm³)	23	KV/mm	IEC 60243
Relative Permittivity (100Hz&1MHz)	3.1	/	IEC 60250
Dissipation Factor (100Hz&1MHz)	0.004	/	IEC 60250
Volume Resistivity	10^15	Ω·cm	IEC 60093
Surface Resistivity	10^15	Ω	IEC 60093
Typical Processing Conditions	**Value**	**Units**	**Test Standard**
Drying Temp. / Time	150℃&4h	/	/
Injection Molding Melt Temp.	355~375	°C	/
Injection Molding Mold Temp.	175~205	°C	/

Disclaimer

Please refer to Material Safety Data before using this product, The information contained in this data sheet is based on tests of research of Sciengy New Materials Co,.Ltd(Sciengy). The user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the users specific application. Sciengy no warranty is given concerning the accuracy or completeness thereof.