Wednesday, May 13, 2026

Plaslube® PEEK CTG30 A 002

Techmer Polymer Modifiers - *Polyetheretherketone*

Units SI

Action **Legend (Open)**

General Information

General		
Material Status	• Commercial: Active	
Availability	• North America	
Filler / Reinforcement	• Carbon Fiber	
Additive	• Graphite Powder Lubricant	• PTFE Lubricant
Features	• Lubricated	
Appearance	• Black	
Processing Method	• Injection Molding	

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.43	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.40	%	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength (Break)	138	MPa	ASTM D638
Tensile Elongation (Break)	1.7	%	ASTM D638
Flexural Modulus	11700	MPa	ASTM D790
Flexural Strength	234	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.22		
vs. Steel - Static	0.19		
Wear Factor	56	10^-8 mm³/N·m	
Limiting Pressure Velocity			ASTM D3702
10 fpm	40000.0	psi·fpm	
100 fpm	45000.0	psi·fpm	
1000 fpm	28000.0	psi·fpm	
Impact	**Nominal Value**	**Unit**	**Test Method**
Notched Izod Impact (23°C, 3.18 mm)	69	J/m	ASTM D256
Hardness	**Nominal Value**	**Unit**	**Test Method**
Rockwell Hardness (R-Scale)	116		ASTM D785
Thermal	**Nominal Value**	**Unit**	**Test Method**
Deflection Temperature Under Load (0.45 MPa, Unannealed)	> 316	°C	ASTM D648
Deflection Temperature Under Load (1.8 MPa, Unannealed)	310	°C	ASTM D648
CLTE - Flow	2.2E-5	cm/cm/°C	ASTM D696
Electrical	**Nominal Value**	**Unit**	**Test Method**
Volume Resistivity	1.0E+4 to 1.0E+6	ohms·cm	ASTM D257

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	149	°C
Drying Time	2.0 to 4.0	hr
Rear Temperature	360 to 388	°C
Middle Temperature	360 to 388	°C
Front Temperature	360 to 388	°C
Processing (Melt) Temp	360 to 382	°C
Mold Temperature	177 to 218	°C
Back Pressure	0.345 to 0.689	MPa

Screw Speed	50 to 100 rpm

Notes

[1] Typical properties: these are not to be construed as specifications.

powered by PROSPECTOR®

www.ulprospector.com

UL LLC ©2026. All rights reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.