Wednesday, May 13, 2026

# Plaslube® PEEK CF30 TL15 HF

**Techmer Polymer Modifiers - *Polyetheretherketone***

Units SI

| Action | Legend (Open) |
|---|---|

## General Information

| General | | |
|---|---|---|
| Material Status | • Commercial: Active | |
| Availability | • North America | |
| Filler / Reinforcement | • Carbon Fiber | |
| Additive | • PTFE Lubricant | |
| Features | • High Flow | • Lubricated |
| Appearance | • Black | |
| Processing Method | • Injection Molding | |

## Properties [1]

| Physical | Nominal Value | Unit | Test Method |
|---|---|---|---|
| Density / Specific Gravity | 1.50 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow (3.18 mm) | 0.10 | % | ASTM D955 |
| Water Absorption (24 hr) | 0.14 | % | ASTM D570 |
| **Mechanical** | **Nominal Value** | **Unit** | **Test Method** |
| Tensile Strength (Break) | 221 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 1.0 | % | ASTM D638 |
| Flexural Modulus | 24800 | MPa | ASTM D790 |
| Flexural Strength | 338 | MPa | ASTM D790 |
| **Impact** | **Nominal Value** | **Unit** | **Test Method** |
| Notched Izod Impact (23°C, 3.18 mm) | 85 | J/m | ASTM D256 |
| **Hardness** | **Nominal Value** | **Unit** | **Test Method** |
| Rockwell Hardness (R-Scale) | 118 | | ASTM D785 |
| **Thermal** | **Nominal Value** | **Unit** | **Test Method** |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 288 | °C | ASTM D648 |
| CLTE - Flow | 1.1E-5 | cm/cm/°C | ASTM D696 |
| **Electrical** | **Nominal Value** | **Unit** | **Test Method** |
| Volume Resistivity | < 1.0E+5 | ohms·cm | ASTM D257 |
| **Flammability** | **Nominal Value** | **Unit** | **Test Method** |
| Flame Rating (0.8 mm) | V-0 | | UL 94 |

## Processing Information

| Injection | Nominal Value | Unit |
|---|---|---|
| Drying Temperature | 149 | °C |
| Drying Time | 2.0 to 4.0 | hr |
| Rear Temperature | 360 to 388 | °C |
| Middle Temperature | 360 to 388 | °C |
| Front Temperature | 360 to 388 | °C |
| Processing (Melt) Temp | 360 to 382 | °C |
| Mold Temperature | 177 to 218 | °C |
| Back Pressure | 0.345 to 0.689 | MPa |
| Screw Speed | 50 to 100 | rpm |

## Notes

[1] Typical properties: these are not to be construed as specifications.

powered by PROSPECTOR®

UL LLC ©2026. All rights reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This

www.ulprospector.com website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.