Zeniva® ZA-600 CF30
polyetheretherketone

Zeniva® ZA-600 CF30 is a carbon-fiber reinforced grade of polyetheretherketone (PEEK) offered for use in implantable devices. The manufacturing facility for Zeniva® PEEK is ISO 13485 registered and the relevant aspects of current Good Manufacturing Practices are also applied.

Our biomaterial manufacturing processes are carefully validated, and enhanced controls provide product traceability. In addition, all materials are tested in a lab that is ISO 17025 accredited.

The chemical, physical, and mechanical properties of finished parts are related to the processes utilized in producing the finished part (for example, molding, machining, annealing, sterilization, etc).

Zeniva® ZA-600 CF30 is offered as compounded pellets.

An FDA MAF is available. In Japan, a PMDA MF is available.

General		
Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• North America
Uses	• Body Implants	• Medical/Healthcare Applications
Agency Ratings	• ISO 10993	• ISO 13485
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.41		ASTM D792

Mechanical	Typical Value	Unit	Test method
Tensile Modulus	26000	MPa	ASTM D638
Tensile Strength (Break)	240	MPa	ASTM D638
Tensile Elongation (Break)	1.8	%	ASTM D638
Flexural Modulus	21000	MPa	ASTM D790
Flexural Strength - (Break)	350	MPa	ASTM D790

Impact	Typical Value	Unit	Test method
Notched Izod Impact	75	J/m	ASTM D256

Thermal	Typical Value	Unit	Test method
Glass Transition Temperature	150	°C	ASTM D3418
Peak Melting Temperature	340	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	290	°C	ASTM D3418

Fill Analysis	Typical Value	Unit	Test method
Melt Viscosity (400°C, 1000 sec^-1)	400	Pa·s	ASTM D3835

Zeniva® ZA-600 CF30
polyetheretherketone

Additional Information	Typical Value Unit	Test method
Cytotoxicity	Pass	ISO 10993:5
Physiochemical Testing	Pass	ISO 10993:18

Notes
Typical properties: these are not to be construed as specifications.

www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2026 2023 Syensqo. All rights reserved.