TECAPEEK SD black - Stock Shapes (rods, plates, tubes)

Chemical Designation
PEEK (Polyetheretherketone)

Colour
black opaque

Density
1.72 g/cm^3

Main features
- electrically static dissipative
- excellent chemical resistance

Target Industries
- semiconductor technology

Mechanical properties	condition	value	unit	test method		comment
Tensile strength	@ 73 °F	18,180	psi	ASTM D 638		(1) Notched
Modulus of elasticity (tensile test)	@ 73 °F	1,200,000	psi	ASTM D 638		
Elongation at break (tensile test)	@ 73 °F	2.3	%	ASTM D 638		
Flexural strength	@ 73 °F	19,900	psi	ASTM D 790		
Modulus of elasticity (flexural test)	@ 73 °F	957,200	psi	ASTM D 790		
Compression strength	1% / 10% strain	7,200/24,640	psi	ASTM D 695		
Compression modulus	@ 73 °F	617,000	psi	ASTM D 695		
Impact strength (Izod)	@ 73 °F	1.08	ft-lbs/in	ASTM D 256	1)	
Shore hardness	D scale	94		ASTM D 2240		
Rockwell hardness	M scale	106		ASTM D 785		

Thermal properties	condition	value	unit	test method		comment
Glass transition temperature		318	°F	-	1)	(1) DSC (2) DSC
Melting temperature		638	°F	-	2)	
Service temperature	short term	572	°F	-		
Service temperature	long term	500	°F	-		
Thermal expansion (CLTE)	73-140°F, long.	2.78	*10^{-5} in/in/°F	DIN EN ISO 11359-1;2		
Thermal expansion (CLTE)	73-212°F, long.	2.78	*10^{-5} in/in/°F	DIN EN ISO 11359-1;2		
Thermal expansion (CLTE)	212-302°F, long.	3.89	*10^{-5} in/in/°F	DIN EN ISO 11359-1;2		

Electrical properties	condition	value	unit	test method	comment
surface resistivity		10^6 - 10^9	Ω	DIN IEC 60093	

Other properties	condition	value	unit	test method	comment
Water absorption	24hr	0.02	%	ASTM D 570	

Information about products and services sold by Ensinger, including without limitation information contained in this document do not constitute a warranty by Ensinger as to the quality and state or durability of products or services, or any guarantee of chemical resistance. Such information reflects the current state of our knowledge and is intended only to assist and advise the recipient. The recipient shall not be entitled to rely on Ensinger provided information and the recipient agrees to evaluate such information, to make an independent decision regarding the suitability of such information, products and services for its application, and only use such products, services and information pursuant to then current good product stewardship principles and all regulatory requirements applicable to the recipient's business. Values are guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. Data sheet values are subject to periodic review and the most recent update can be found at www.ensingerplastics.com

Ensinger Inc. Headquarters 365 Meadowlands Boulevard Washington, PA 15301, USA
Phone 800-243-3221 Sales Phone 800-869-4029
Technical Fax 724-746-9209
sales@ensingerusa.com

Date: 2018/04/25
Version: A0