Wednesday, May 13, 2026

HiFill® PEEK 0162 T1 L MB

Techmer Polymer Modifiers - *Polyetheretherketone*

Units SI

Action **Legend (Open)**

General Information

General	
Material Status	• Commercial: Active
Availability	• North America
Features	• Low Viscosity
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.60	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.0	%	ASTM D955
Water Absorption (24 hr)	0.12	%	ASTM D570
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength (Yield)	79.3	MPa	ASTM D638
Tensile Elongation (Yield)	6.5	%	ASTM D638
Flexural Modulus	4480	MPa	ASTM D790
Flexural Strength	152	MPa	ASTM D790
Impact	**Nominal Value**	**Unit**	**Test Method**
Notched Izod Impact (23°C, 3.18 mm)	130	J/m	ASTM D256
Hardness	**Nominal Value**	**Unit**	**Test Method**
Rockwell Hardness (R-Scale)	105		ASTM D785
Thermal	**Nominal Value**	**Unit**	**Test Method**
Deflection Temperature Under Load (1.8 MPa, Unannealed)	> 260	°C	ASTM D648
CLTE - Flow	4.7E-5	cm/cm/°C	ASTM D696
Electrical	**Nominal Value**	**Unit**	**Test Method**
Surface Resistivity	> 1.0E+15	ohms	ASTM D257
Volume Resistivity	> 1.0E+13	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	16	kV/mm	ASTM D149
Dielectric Constant [2]	3.50		ASTM D150
Dissipation Factor	5.0E-3		ASTM D150

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	149	°C
Drying Time	2.0 to 4.0	hr
Rear Temperature	360 to 388	°C
Middle Temperature	360 to 388	°C
Front Temperature	360 to 388	°C
Processing (Melt) Temp	360 to 382	°C
Mold Temperature	177 to 218	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	50 to 100	rpm

Notes

[1] Typical properties: these are not to be construed as specifications.

[2] 1KHz

powered by PROSPECTOR® UL LLC ©2026. All rights reserved.

www.ulprospector.com

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.