Edgetek™ PK-30GF/000 BK

Polyetheretherketone

Key Characteristics

Product Description		
30% Glass Fiber Reinforced PEEK Compound with Standard Flowability		
General		
Material Status	• Commercial: Active	
Regional Availability	• Asia Pacific	
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight	
Features	• General Purpose	• High Heat Resistance
Uses	• Automotive Applications • Consumer Applications	• General Purpose • Industrial Applications
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Injection Molding	

Technical Properties [1]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.48	1.48	ASTM D792
Melt Mass-Flow Rate (MFR) (400°C/2.16 kg)	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Molding Shrinkage - Flow	2.0E-3 to 4.0E-3 in/in	0.20 to 0.40 %	ASTM D955
Mechanical	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Modulus [2]	1.89E+6 psi	13000 MPa	ASTM D638
Tensile Strength [2] (Yield)	26100 psi	180 MPa	ASTM D638
Tensile Elongation [2] (Break)	3.0 to 4.0 %	3.0 to 4.0 %	ASTM D638
Flexural Modulus	1.74E+6 psi	12000 MPa	ASTM D790
Flexural Strength	40600 psi	280 MPa	ASTM D790
Impact	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Notched Izod Impact			ASTM D256A
73°F (23°C), 0.125 in (3.18 mm), Injection Molded	2.2 ft·lb/in	120 J/m	
Unnotched Izod Impact			ASTM D4812
73°F (23°C), 0.125 in (3.18 mm)	18 ft·lb/in	950 J/m	
Thermal	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm)	617 °F	325 °C	
Electrical	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Surface Resistivity	1.0E+14 ohms	1.0E+14 ohms	ASTM D257
Flammability	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Flame Rating (0.06 in (1.6 mm))	V-0	V-0	Internal Method

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	302 to 320 °F	150 to 160 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Processing (Melt) Temp	680 to 734 °F	360 to 390 °C
Mold Temperature	338 to 374 °F	170 to 190 °C

Injection Notes

Injection Pressure: MED-HIGH
Hold Pressure: MED-HIGH
Screw Speed: MODERATE
Back Pressure: LOW

Notes

[1] Typical values are not to be construed as specifications.

[2] Type I, 0.20 in/min (5.1 mm/min)

CONTACT INFORMATION

North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.