Zeniva® ZA-600
polyetheretherketone

Zeniva® ZA-600 is a grade of polyetheretherketone (PEEK) offered for use in implantable devices. The manufacturing facility for Zeniva® PEEK in Alpharetta, GA is ISO 13485 registered and the relevant aspects of current Good Manufacturing Practices are also applied.

Our biomaterial manufacturing processes are carefully validated, and enhanced controls provide product traceability. In addition, all materials are tested in a lab that is ISO 17025 accredited. This product meets the requirements of the current version of ASTM F 2026.

The chemical, physical, and mechanical properties of finished parts are related to the processes utilized in producing the finished part (for example, molding, machining, annealing, sterilization, etc).

Zeniva® ZA-600 is offered as resin pellets.

An FDA MAF is available.

General		
Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• North America
Uses	• Body Implants	• Medical/Healthcare Applications
Agency Ratings	• ASTM F2026 • ISO 10993	• ISO 13485
Forms	• Pellets	

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.30		ASTM D792

Mechanical	Typical Value	Unit	Test method
Tensile Modulus	3900	MPa	ASTM D638
Tensile Strength (Yield)	100	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	5.5	%	
Break	20	%	
Flexural Modulus	4000	MPa	ASTM D790
Flexural Strength (Yield)	153	MPa	ASTM D790

Impact	Typical Value	Unit	Test method
Notched Izod Impact	53	J/m	ASTM D256

Thermal	Typical Value	Unit	Test method
Glass Transition Temperature	150	°C	ASTM D3418
Peak Melting Temperature	340	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	290	°C	ASTM D3418

Zeniva® ZA-600
polyetheretherketone

Fill Analysis	Typical Value	Unit	Test method
Melt Viscosity (400°C, 1000 sec^-1)	150	Pa·s	ASTM D3835

Additional Information	Typical Value	Unit	Test method
Cytotoxicity	Pass		ISO 10993:5
Physiochemical Testing	Pass		ISO 10993:18

Notes
Typical properties: these are not to be construed as specifications.

www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2026 2023 Syensqo. All rights reserved.