EK-SGHWF80
Polyetheretherketone (PEEK)

TECHNICAL DATA SHEET

Description

Sciengy® EK-SGHWF80 is a special formular PEEK compound developed to provide excellent wear resistance, lower coefficient of friction and better chemical resistant.

CF+PTFE+graphite, Low Friction and Wear

Series	Special Functional
ISO Designation	>PEEK+PTFE-(CF+G)30<
Process Method	Injection molding

Properties

Physical	**Value**	**Units**	**Test Standard**
Density	1.43	g/cm³	ISO 1183
Mold Shrinkage (Machine Direction)	0.20	%	GB/T 15585
Mold Shrinkage (Transverse Direction)	0.50	%	GB/T 15585
Friction Coefficient (23℃)	0.15	-	GB/T 3960
Mass Wear Loss (23℃)	0.80	mg	GB/T 3960
Flammability(1.6 mm)	V-0		IEC60695
Mechanical	**Value**	**Units**	**Test Standard**
Tensile Stress at Break (5 mm/min)	200	MPa	ISO 527
Tensile Modulus at Break (1 mm/min)	15.0	GPa	ISO 527
Elongation at Break (23℃)	1.8	%	ISO 527
Flexural Modulus at Break (23℃)	14.0	GPa	ISO 178
Flexural Strength at Break	280	MPa	ISO 178
Notched Izod Impact Strength @23℃ (V-notched)	5.0	kJ/m²	ISO 180
Thermal	**Value**	**Units**	**Test Standard**
Melting Temperature (10°C/min)	343	°C	ISO 11357
Glass Transition (Tg)	150	°C	ISO 11357
Electrical Properties	**Value**	**Units**	**Test Standard**
Typical Processing Conditions	**Value**	**Units**	**Test Standard**
Drying Temp. / Time	150℃&3h or 120℃&5h(residual moisture<0.02%)		
Injection Molding Melt Temp.	170℃~200℃		

EK-SGHWF80
Polyetheretherketone (PEEK)

TECHNICAL DATA SHEET

Temperature Settings	365/370/375/385/385℃(Nozzle)		
Hopper Temperature	Not greater than 100℃		
Gate	>2mm or 0.5*part thickness		

Disclaimer

Please refer to Material Safety Data before using this product, The information contained in this data sheet is based on tests of research of Sciengy New Materials Co,.Ltd(Sciengy). The user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the users specific application. Sciengy no warranty is given concerning the accuracy or completeness thereof.