Wednesday, May 13, 2026

Plaslube® PEEK 13005

Techmer Polymer Modifiers - *Polyetheretherketone*

Units SI

Action | **Legend (Open)**

General Information

General		
Material Status	• Commercial: Active	
Availability	• North America	
Features	• High Viscosity	• Lubricated
Appearance	• Colors Available	
Processing Method	• Injection Molding	

Properties [1]

Physical	**Nominal Value**	**Unit**	**Test Method**
Density / Specific Gravity	1.36	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.60	%	ASTM D955
Water Absorption (24 hr)	0.12	%	ASTM D570
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength (Yield)	96.5	MPa	ASTM D638
Tensile Elongation (Yield)	2.0	%	ASTM D638
Flexural Modulus	6210	MPa	ASTM D790
Flexural Strength	193	MPa	ASTM D790
Impact	**Nominal Value**	**Unit**	**Test Method**
Notched Izod Impact (23°C, 3.18 mm)	80	J/m	ASTM D256
Hardness	**Nominal Value**	**Unit**	**Test Method**
Rockwell Hardness (R-Scale)	105		ASTM D785
Thermal	**Nominal Value**	**Unit**	**Test Method**
Deflection Temperature Under Load (1.8 MPa, Unannealed)	232	°C	ASTM D648
CLTE - Flow	4.7E-5	cm/cm/°C	ASTM D696
Electrical	**Nominal Value**	**Unit**	**Test Method**
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength	12	kV/mm	ASTM D149
Flammability	**Nominal Value**	**Unit**	**Test Method**
Flame Rating (0.8 mm)	V-0		UL 94

Processing Information

Injection	**Nominal Value**	**Unit**
Drying Temperature	149	°C

Notes

[1] Typical properties: these are not to be construed as specifications.

powered by PROSPECTOR®

www.ulprospector.com

UL LLC ©2026. All rights reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.