Wednesday, May 13, 2026

HiFill® PEEK 4150 A YAG BK107 - Ver 2

Techmer Polymer Modifiers - *Polyetheretherketone*

Units SI

Action **Legend (Open)**

General Information

General	
Material Status	• Commercial: Active
Availability	• North America
Features	• Laser Markable
Appearance	• Black
Processing Method	• Injection Molding

Properties [1]

Physical	**Nominal Value**	**Unit**	**Test Method**
Density / Specific Gravity	1.28	g/cm³	ASTM D792
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Modulus	3450	MPa	ASTM D638
Tensile Strength (Yield)	86.2	MPa	ASTM D638
Tensile Strength (Break)	75.8	MPa	ASTM D638
Tensile Elongation (Break)	30	%	ASTM D638
Impact	**Nominal Value**	**Unit**	**Test Method**
Notched Izod Impact (3.18 mm)	80	J/m	ASTM D256

Processing Information

Injection	**Nominal Value**	**Unit**
Drying Temperature	149	°C
Drying Time	3.0 to 4.0	hr
Rear Temperature	377 to 399	°C
Middle Temperature	377 to 399	°C
Front Temperature	377 to 399	°C
Nozzle Temperature	377 to 399	°C
Processing (Melt) Temp	377 to 399	°C
Mold Temperature	193 to 204	°C
Injection Rate	Slow-Moderate	
Back Pressure	0.345 to 0.689	MPa
Screw Speed	Slow	

Notes

[1] Typical properties: these are not to be construed as specifications.

powered by PROSPECTOR®

UL LLC ©2026. All rights reserved.

www.ulprospector.com

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.