Sarlink® TPE EE-2270B-01 BLK

Teknor Apex Company - Thermoplastic Elastomer

Friday, April 3, 2026

General Information

Product Description

Sarlink EE-2270B-01 BLACK is a general purpose thermoplastic elastomer designed for automotive applications, including exterior extruded components. Sarlink EE-2270B-01 BLACK is a medium hardness, low density, filled grade with good UV resistance designed for extrusion.

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Filled • Good Melt Strength • Good Processability • Good Processing Stability	• Good Strength • Halogen Free • High Elongation • Light Stabilized • Low Density	• Low Flow • Low Specific Gravity • Lubricated • Medium Hardness • Slip
Uses	• Automotive Applications • Automotive Exterior Parts	• Automotive Exterior Trim • Automotive Interior Parts	• Grommets • Weatherstripping
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Extrusion		

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	5.0	g/10 min	ASTM D1238
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress [2]			ISO 37
Across Flow : 100% Strain	306	psi	
Flow : 100% Strain	403	psi	
Tensile Stress [2]			ISO 37
Across Flow : Break	1540	psi	
Flow : Break	1120	psi	
Tensile Elongation [2]			ISO 37
Across Flow : Break	770	%	
Flow : Break	610	%	
Tear Strength [3]			ISO 34-1
Across Flow	200	lbf/in	
Flow	206	lbf/in	
Compression Set [4]			ISO 815
73°F, 22 hr	24	%	
158°F, 22 hr	52	%	
194°F, 70 hr	65	%	
257°F, 70 hr	81	%	
Hardness	**Nominal Value**	**Unit**	**Test Method**
Shore Hardness			ISO 868
Shore A, 1 sec, Injection Molded	72		
Shore A, 5 sec, Injection Molded	68		
Shore A, 15 sec, Injection Molded	67		

Revision Date: 7/18/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Sarlink® TPE EE-2270B-01 BLK

Teknor Apex Company - Thermoplastic Elastomer

Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air [5]			ISO 188
Across Flow : 230°F, 1008 hr	3.7	%	
Flow : 230°F, 1008 hr	-0.40	%	
Across Flow : 100% Strain 230°F, 1008 hr	13	%	
Flow : 100% Strain 230°F, 1008 hr	7.6	%	
Across Flow : 257°F, 168 hr	-0.90	%	
Flow : 257°F, 168 hr	-3.9	%	
Across Flow : 100% Strain 257°F, 168 hr	11	%	
Flow : 100% Strain 257°F, 168 hr	9.4	%	
Change in Tensile Strain at Break in Air [5]			ISO 188
Across Flow : 230°F, 1008 hr	-1.6	%	
Flow : 230°F, 1008 hr	0.0	%	
Across Flow : 257°F, 168 hr	-3.9	%	
Flow : 257°F, 168 hr	-3.3	%	
Change in Shore Hardness in Air			ISO 188
Shore A, 230°F, 1008 hr [6]	6.4		
Shore A, 230°F, 1008 hr [7]	6.1		
Shore A, 230°F, 1008 hr [8]	4.9		
Shore A, 257°F, 168 hr [6]	4.4		
Shore A, 257°F, 168 hr [7]	4.0		
Shore A, 257°F, 168 hr [8]	3.3		

Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (392°F, 206 sec^-1)	244	Pa·s	ASTM D3835

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	380 to 400	°F
Cylinder Zone 2 Temp.	390 to 410	°F
Cylinder Zone 3 Temp.	400 to 420	°F
Cylinder Zone 4 Temp.	400 to 420	°F
Cylinder Zone 5 Temp.	410 to 430	°F
Die Temperature	420 to 440	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Revision Date: 7/18/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Sarlink® TPE EE-2270B-01 BLK

Teknor Apex Company - Thermoplastic Elastomer

Notes

[1] Typical properties: these are not to be construed as specifications.

[2] Type 1, 20 in/min

[3] Method Ba, Angle (Unnicked), 20 in/min

[4] Type A

[5] Type 1

[6] 15 sec

[7] 5 sec

[8] 1 sec

Teknor Apex Company
Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan 22
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknoapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 7/18/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector