TECHNICAL DATASHEET

TRIEL® 5300

TPEE

PROPERTY	UNIT	ASTM METHOD	TYPICAL DATA
PHYSICAL			
Specific Gravity	-	D792	1.10
Water Absorption (24 hours at 23℃)	%	D570	0.5
Melt Flow Rate (230도, 2.16kg)	g/10min	D1238	28
MECHANICAL			
Tensile Strength at yield	$kg_f/㎠$	D638	130
Tensile Elongation at break	%	D638	>400
Flexural Strength at yield	$kg_f/㎠$	D790	23
Flexural Modulus	$kg_f/㎠$	D790	365
Izod Impact Strength, notched, 23℃ (1/8")	$kg_f·㎝/㎝$	D256	No Break
Hardness (Shore D)	Shore D		30
THERMAL			
HDT, 4.6 kgf/㎠	℃		52
Vicat softening temperature	℃		108
ELECTRICAL			
OTHERS			
UL-94 Flammability (1/16")	-	(UL 94)	HB
Mold Shrinkage	%		1.8

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

PROCESSING GUIDE

TRIEL® 5300 GRADE

TPEE

- General processing conditions for TRIEL5300 are shown below. Drying prior to processing is essential to ensure desired appearance and property performance.

SPECIFICATION	UNIT	CONDITIONS
Drying Temperature	℃	90~110
Drying Time	hr	3~4
Moisture Content, Max	%	0.02
Melt Temperature	℃	180~210
Nozzle Temperature	℃	180~210
Front Temperature	℃	180~210
Middle Temperature	℃	180~210
Rear Temperature	℃	170~190
Mold Temperature	℃	30~50
Back Pressure	MPa	0.0~0.1
Screw Speed	rpm	10~50
Vent Depth	mm	0.02~0.08

Global Network

HEAD OFFICE
Samyang Corporation
31, Jong-ro 33-gil, Jongno-gu, Seoul, Korea
T. +82-2-740-7747

Chemical Research Center
730, Daedeok-daero, Yuseong-gu, Daejeon, Korea
T. +82-42-865-8114

JEONJU ENGINEERING PLASTIC PLANT
147, Palbok-ro, Deokjin-gu, Jeonju, Korea
T. +82-63-210-6664

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.
No.131, Shuangying Road, Qingpu Industrial Area,
Qingpu County, Shanghai, China
T. +86-21-6922-2270

SAMYANG ENGINEERING PLASTICS (HUNGARY) CO., LTD.
H5100, Jaszbereny, Necso, Telep 1, Hungary
T. +36-21-311-1263

SAMYANG ENGINEERING PLASTICS (VIETNAM) LLC
1 Song Hanh Road, Nhon Trach 6 Industrial Zone, Long Tho
Commune, Nhon Trach District, Dong Nai Province, Vietnam
T. +84-0251-3686-707