ColorFast® PVDF

Product Description COLORED PVDF

Material Status Commercial: Active

Availability Africa & Middle East, Asia Pacific, Europe, Latin America, North America

Features Excellent Colorability

Uses Aerospace Applications, Connectors, Consumer Applications, Engineering Parts, Industrial Applications, Industrial Parts, Military/Defense Applications, Oil/Gas Applications, Outdoor Applications

Forms Pellets

Processing Method Injection Molding

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.78	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	2.0	%	ASTM D955

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2210	MPa	ASTM D638
Tensile Strength	53.8	MPa	ASTM D638
Tensile Elongation (Yield)	> 10	%	ASTM D638
Flexural Modulus	2140	MPa	ASTM D790
Flexural Strength	62.1	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	110	J/m	ASTM D256

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	ASTM D257

Injection	Nominal Value	Unit
Drying Temperature	121	°C
Drying Time	4.0	hr
Processing (Melt) Temp	216 to 232	°C
Mold Temperature	66 to 93	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm

Notes

[1] Typical properties: these are not to be construed as specifications.

Properties provided are only typical values and Americhem assumes no liability for the customer's use of the information provided. The customer assumes all responsibility for testing determining this products suitability in the customer's specific end application.

Revision Date: 6/3/2026

Americhem World Headquarters
2000 Americhem Way
Cuyahoga Falls, OH 44221
Tel: +1 330 929 4213
Toll Free: +1 800 228 3476

Americhem Engineered Compounds
20 Progress Drive
Morrisvillle, PA 19067
Tel: +1 215 736 1126
Toll Free: +1 800 863 4260