Sarlink® TPE ML-1670B BLK

Teknor Apex Company - Thermoplastic Elastomer

Friday, April 3, 2026

General Information

Product Description

Sarlink ML-1600 series is a high performance, high flow thermoplastic elastomer series, available in NAT and BLK designed for automotive interior applications. Sarlink ML-1670B BLK is a medium hardness, medium density grade with excellent surface appearance suitable for injection molding.

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Filled • Good Adhesion • Good Flexibility • Good Moldability	• Good Processability • Good Surface Finish • Good Tear Strength • Good Toughness • High Flow	• Medium Density • Medium Hardness • Resilient
Uses	• Automotive Applications • Automotive Interior Parts • Flexible Grips	• Grommets • Knobs • Rubber Replacement	• Soft Touch Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density	0.990	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	27	g/10 min	ASTM D1238
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress [2]			ISO 37
Across Flow : 100% Strain	290	psi	
Flow : 100% Strain	390	psi	
Tensile Stress [2]			ISO 37
Across Flow : Break	972	psi	
Flow : Break	899	psi	
Tensile Elongation [2]			ISO 37
Across Flow : Break	800	%	
Flow : Break	700	%	
Tear Strength [3]			ISO 34-1
Across Flow	147	lbf/in	
Flow	152	lbf/in	
Compression Set [4]			ISO 815
73°F, 22 hr	27	%	
158°F, 22 hr	46	%	
194°F, 70 hr	68	%	
257°F, 70 hr	93	%	

Revision Date: 6/24/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Sarlink® TPE ML-1670B BLK

Teknor Apex Company - Thermoplastic Elastomer

Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A, 1 sec, Injection Molded	73		
Shore A, 5 sec, Injection Molded	70		
Shore A, 15 sec, Injection Molded	68		

Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air [5]			ISO 188
Across Flow : 230°F, 1008 hr	3.3	%	
Flow : 230°F, 1008 hr	-3.6	%	
Across Flow : 100% Strain 230°F, 1008 hr	9.7	%	
Flow : 100% Strain 230°F, 1008 hr	13	%	
Across Flow : 257°F, 168 hr	9.8	%	
Flow : 257°F, 168 hr	0.0	%	
Across Flow : 100% Strain 257°F, 168 hr	5.9	%	
Flow : 100% Strain 257°F, 168 hr	10	%	
Change in Tensile Strain at Break in Air [5]			ISO 188
Across Flow : 230°F, 1008 hr	-5.1	%	
Flow : 230°F, 1008 hr	-4.8	%	
Across Flow : 257°F, 168 hr	11	%	
Flow : 257°F, 168 hr	7.2	%	
Change in Shore Hardness in Air			ISO 188
Shore A, 230°F, 1008 hr [6]	3.6		
Shore A, 230°F, 1008 hr [7]	3.1		
Shore A, 230°F, 1008 hr [8]	2.9		
Shore A, 257°F, 168 hr [6]	3.3		
Shore A, 257°F, 168 hr [7]	2.7		
Shore A, 257°F, 168 hr [8]	1.8		

Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (392°F, 206 sec^-1)	111	Pa·s	ASTM D3835

Additional Information	Nominal Value	Unit	Test Method
Xenon Weatherometer			SAE J1885
Delta E - 1250 kJ	1.30		
Delta E - 2500 kJ	1.30		

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F

Revision Date: 6/24/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Sarlink® TPE ML-1670B BLK

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

[1] Typical properties: these are not to be construed as specifications.

[2] Type 1, 20 in/min

[3] Method Ba, Angle (Unnicked), 20 in/min

[4] Type A

[5] Type 1

[6] 15 sec

[7] 5 sec

[8] 1 sec

Teknor Apex Company
Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan 22
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknoapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 6/24/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector