Sunday, September 20, 2026

MHCompounds Wire & Cable
TPE 5970 LSZH

Units English

M. Holland Company -
Thermoplastic Elastomer

Action **Legend (Open)**

General Information

Product Description

TPE 5970 LSZH is a natural thermoplastic elastomer (TPE) intended for wire and cable jacketing applications where maximum flame resistance is required. TPE 5970 LSZH has a very low heat release when measured in the cone calorimeter per ASTM E 1354-11b. Smoke k(1/m) measurements are very low when compared to halogen or conventional metal hydrate compounds.

TPE 5970 LSZH contains a novel non-halogen intumescent flame retardant additive package designed to reduce normal flame spread characteristics and achieve a VW-1 flame resistant rating on 18 AWG wires and larger. It also offers good extrusion processing characteristics on either conventional polyethylene or PVC extrusion lines. In addition, TPE 5970 LSZH contains a UV stabilization additive package that provides effective long-term UV weather resistance.

TPE 5970 LSZH is readily pigmented to a variety of colors using standard wire and cable color concentrates designed for thermoplastic or crosslinked polyolefins.

Application
TPE 5970 LSZH is intended for use as a plenum or riser cable jacket. This product is rated a V-0 by UL Standard 94 at a minimum thickness of 0.062 inches. TPE 5970 LSZH is expected to achieve a VW-1 flame resistance on 18 AWG or larger conductors as per UL Standard 1581.

General			
Material Status	• Preliminary Data		
Availability	• North America		
Additive	• Flame Retardant	• UV Stabilizer	
Features	• Flame Retardant • Good Colorability	• Good Flexibility • Halogen Free	• UV Resistant
Uses	• Jacketing	• Wire & Cable Applications	
Agency Ratings	• UL 1277 • UL 1581	• UL 1666 • UL 444	• UL 758, Style 1722 • UL VW-1
Appearance	• Natural Color		
Processing Method	• Extrusion		

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.36		ASTM D792
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Flexural Modulus [2] (0.0300 in)	59100	psi	ASTM D790
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength (0.0300 in)	756	psi	ASTM D412
Tensile Elongation (Break, 0.0300 in)	210	%	ASTM D412
Hardness	**Nominal Value**	**Unit**	**Test Method**
Durometer Hardness (Shore A, 15 sec, 0.0300 in)	98		ASTM D2240
Thermal	**Nominal Value**	**Unit**	**Test Method**
Heat Deformation [3] (302°F, 30.0 mil)	6.0	%	UL 2556
Aging	**Nominal Value**	**Unit**	**Test Method**
Retention of Tensile Elongation - 7 days at 158°C (30.0 mil)	100	%	UL 1581
Retention of Tensile Strength - 7 days at 158°C (30.0 mil)	81	%	UL 1581
Flammability	**Nominal Value**	**Unit**	**Test Method**
Flame Rating	V-0		UL 94
Oxygen Index	70	%	ASTM D2863

Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	370	°F
Cylinder Zone 2 Temp.	385	°F
Cylinder Zone 3 Temp.	390	°F

Cylinder Zone 4 Temp.	390 °F
Melt Temperature	390 °F
Die Temperature	395 °F

Notes

[1] Typical properties: these are not to be construed as specifications.

[2] Chord Modulus (0.5 to 1.0%)

[3] 2000 g

Corporate Offices:
400 Skokie Boulevard, Suite 600
Northbrook, IL 60062
800.872.7370
In Illinois: 847.272.7370
Customer Service FAX: 847.272.7713

UL and the UL logo are trademarks of UL LLC ©, 2026. All Rights Reserved. UL PROSPECTOR

The information presented on this datasheet was acquired by UL IDES from the producer of the material. UL IDES makes substantial efforts to assure the accuracy of this data. However, UL IDES assumes no responsibility for the data values and strongly encourages that upon final material selection, data points are validated with the material supplier.