TECAFLON® PVDF natural - Stock Shapes (rods, plates, tubes)

Chemical Designation
PVDF (Polyvinylidene fluoride)

Colour
white

Density
1.78 g/cm^3

Main features
- excellent chemical resistance
- inherent flame resistance
- high gamma radiation resistance
- good UV and weather resistance
- good mechanical properties
- low moisture absorption
- good machinability

Target Industries
- chemical plant engineering
- process engineering
- medical technology
- cleanroom technology
- food processing
- food engineering

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	350,000	psi	ASTM D 638	
Tensile strength at yield	@ 73 °F	8,100	psi	ASTM D 638	
Tensile strength at break	@ 73 °F	7,800	psi	ASTM D 638	
Elongation at break (tensile test)	@ 73 °F	35	%	ASTM D 638	
Flexural strength	@ 73 °F	9,700	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	320,000	psi	ASTM D 790	
Compression strength	@ 73 °F, 10% strain	11,600	psi	ASTM D 695	
Compression	@ 73 °F, 1% strain	3,200	psi	ASTM D 695	
Compression modulus	@ 73 °F	160,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	2.49	ft-lbs/in	ASTM D 256	
Rockwell hardness	@ 73 °F, M scale	79		ASTM D 785	

Thermal properties	condition	value	unit	test method		comment
Melting temperature		346	°F	ASTM D 3418		(1) publicly sourced data (2) Injection molded samples (3) Data obtained from public source (4) Data obtained from public source (5) publicly sourced data (6) publicly sourced data
Deflection temperature	@264 psi	235	°F	ASTM D 648	1)	
Deflection temperature	@ 66 psi	300	°F	ASTM D 648	2)	
Service temperature	short term	300	°F	-	3)	
Service temperature	Long Term	300	°F	-	4)	
Thermal expansion (CLTE)		$7.1*10^{-5}$	in/in/°F	ASTM D 696	5)	
Thermal conductivity		1.32	BTU-in/hr-ft^2-°F	ASTM C 177	6)	

Electrical properties	condition	value	unit	test method		comment
volume resistance	@ 73 °F	$5*10^{14}$	Ω*cm	ASTM D 257	1)	(1) publicly sourced data (2) Injection molded samples (3) publicly sourced data (4) publicly sourced data
Dielectric strength		510	V/mil	ASTM D 149	2)	
Dissipation factor	@ 60 Hz, 73 °F	0.06		ASTM D 150	3)	
Dielectric constant	@ 60 Hz, 73 °F, 50% RH	9		ASTM D 150	4)	

Other properties	condition	value	unit	test method		comment
Moisture absorption	@ 24 hrs, 73 °F	0.02	%	ASTM D 570		(1) Thickness greater than 0.1 mm Injection molded samples
Flammability (UL94)		V0		-	1)	

- Resin specification:
  ASTM D3222-18a Type II
  Shapes specification:
  ASTM D6713-24 S-PVDF0110 X0000000 & ASTM D8366 Class A Type II Grade N/A

Information about products and services sold by Ensinger, including without limitation information contained in this document do not constitute a warranty by Ensinger as to the quality and state or durability of products or services, or any guarantee of chemical resistance. Such information reflects the current state of our knowledge and is intended only to assist and advise the recipient. The recipient shall not be entitled to rely on Ensinger provided information and the recipient agrees to evaluate such information, to make an independent decision regarding the suitability of such information, products and services for its application, and only use such products, services and information pursuant to then current good product stewardship principles and all regulatory requirements applicable to the recipient's business. Values are guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. Data sheet values are subject to periodic review and the most recent update can be found at www.ensingerplastics.com

Ensinger Inc. Headquarters 365 Meadowlands Boulevard Washington, PA 15301, USA
Phone 800-243-3221 Sales Phone 800-869-4029
Technical Fax 724-746-9209
sales@ensingerusa.com
Date: 2023/06/21
Version: A1