Telcar® SGI 70076

Teknor Apex Asia Pacific PTE. LTD. - Thermoplastic Elastomer

Tuesday, April 7, 2026

General Information

General			
Material Status	• Commercial: Active		
Availability	• Asia Pacific		
Uses	• Flexible Grips • Handles	• Plugs • Shock Absorbing Pads	• Toys
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.00		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	7.0	g/10 min	ASTM D1238
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress (100% Strain)	725	psi	ASTM D412
Tensile Strength (Break)	870	psi	ASTM D412
Tensile Elongation (Break)	200	%	ASTM D412
Hardness	**Nominal Value**	**Unit**	**Test Method**
Durometer Hardness (Shore A, 10 sec)	70		ASTM D2240

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	104 to 176	°F
Rear Temperature	284 to 356	°F
Middle Temperature	284 to 356	°F
Front Temperature	284 to 356	°F
Mold Temperature	104 to 140	°F
Injection Pressure	300 to 3000	psi
Injection Rate	Slow-Moderate	

Injection Notes

Purging Material: HDPE, PP

Extrusion	Nominal Value	Unit
Drying Temperature	104 to 176	°F
Cylinder Zone 1 Temp.	284 to 356	°F
Cylinder Zone 2 Temp.	284 to 356	°F
Cylinder Zone 3 Temp.	284 to 356	°F
Cylinder Zone 4 Temp.	284 to 356	°F
Cylinder Zone 5 Temp.	284 to 356	°F

Extrusion Notes

Compression Ratio: 2.0 to 4.0
Purging Material: HDPE, PP
LD Ratio: 25:1 or higher

Notes

[1] Typical properties: these are not to be construed as specifications.

Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Telcar® SGI 70076

Teknor Apex Asia Pacific PTE. LTD. - Thermoplastic Elastomer

Teknor Apex Company
Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan 22
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknoapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector