TECHNICAL DATASHEET

Grilamid L XE 11370 black

PA12

EMS-GRIVORY
Material Database

Physical
Low moisture absorption

Chemical
Excellent chemical resistance

Mechanical
Good abrasion resistance

Processing
Coating, Other extrusion

Delivery form
Granules

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Product Information

Product-nomenclature: ISO 16396-PA12,EHL1Z,C16-010

Mechanical Properties	dry/cond	Unit	Standard
Tensile modulus	1800 / 1400	MPa	ISO 527
Yield stress	50 / 50	MPa	ISO 527
Yield strain	15 / 18	%	ISO 527
Nominal strain at break	35 / 45	%	ISO 527
Charpy impact strength, +23°C	N / N	kJ/m²	ISO 179/1eU
Charpy impact strength, -30°C	40 / 40	kJ/m²	ISO 179/1eU
Charpy notched impact strength, +23°C	10 / 15	kJ/m²	ISO 179/1eA
Charpy notched impact strength, -30°C	9 / 7	kJ/m²	ISO 179/1eA
Ball indentation hardness	85 / 70	MPa	ISO 2039-1

Thermal Properties	dry/cond	Unit	Standard
Melting temperature, 10°C/min	178 / -	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	60 / -	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	130 / -	°C	ISO 75-1/-2

Electrical Properties	dry/cond	Unit	Standard
Surface resistivity	- / 1000	Ohm	IEC 62631-3-2

General Properties	dry/cond	Unit	Standard
Density	1040 / -	kg/m³	ISO 1183
Burning behav. at thickness h	HB / -	class	IEC 60695-11-10
Thickness tested	0.8 / -	mm	
Water absorption	1.4 / -	%	Sim. to ISO 62
Humidity absorption	0.5 / -	%	Sim. to ISO 62

Grilamid L XE 11370 black

Processing Extrusion	Value	Unit	Standard
Length	24 - 25	mm	
Compression ratio	2 - 2.5		
Conveying zone	220 - 240	°C	
Compression zone	230 - 250	°C	
Metering zone	230 - 250	°C	
Melt	230 - 260	°C	
Die	230 - 250	°C	
Adapter	230 - 250	°C	

EMS-CHEMIE AG
Business Unit EMS-GRIVORY

Homepage: EMS-GRIVORY
eMail: welcome@emsgrivory.com

The values are intended to serve as an aid in preselecting materials and for an overview of the EMS-GRIVORY product range. The information contained in this publication is based on our present knowledge and experience. The given figures and data are guidance values and do not represent binding material specifications. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are given regarding products, design, data and information. The customer is not released from his obligation to investigate the products fitness and the suitability for the intended application, compliance with legal requirements and intellectual property rights. We reserve the right to change the information at any time and without prior notice. The information in this publication is not to be considered a contractual obligation and any liability whatsoever is expressly declined. For further questions about our products please contact our experts.

Created: Aug 25, 2026