Renol™ SPD-M DEEP RED/46P-115/144724-16

Thermoplastic Elastomer

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Europe
Forms	• Pellets

Technical Properties [1]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.20	1.20	ASTM D792
Molding Shrinkage - Flow	8.0E-3 to 0.015 in/in	0.80 to 1.5 %	ASTM D955
Mechanical	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Modulus - 100% Secant	1020 psi	7.00 MPa	ASTM D638
Tensile Strength (Break)	3920 psi	27.0 MPa	ASTM D638
Tensile Elongation (Break)	580 %	580 %	ASTM D638
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Shore Hardness (15 sec)	85 to 90	85 to 90	ISO 868

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature - Desiccant Dryer	176 °F	80 °C
Drying Time - Desiccant Dryer	2.0 hr	2.0 hr
Suggested Max Moisture	0.10 %	0.10 %
Processing (Melt) Temp	356 to 428 °F	180 to 220 °C
Mold Temperature	68 to 104 °F	20 to 40 °C

Notes

[1] Typical values are not to be construed as specifications.

CONTACT INFORMATION

North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.