BARLOG Plastics
Mehr aus Polymer.

Technical data
KEBAFLEX / U D63 ST B.01

KEBAFLEX / U D63 ST B.01 is a TPU with a Shore hardness of 63D. It is characterized by flexibility and good wear and abrasion resistance.

Polymer: TPE-U

ISO designation: TPE-U

Productgroup: TPE

Brief description of the product family:

The trade name KEBAFLEX / U stands for a range of thermoplastic polyurethane elastomers. KEBAFLEX / U is characterized by excellent sliding and wear behavior, suitability for use at elevated temperatures, good UV resistance and high mechanical load-bearing capacity.

Properties:

flexible, good gliding properties, good recovery behavior, High wear resistance, impact resistant, PFAS-free

Typical areas of application:

Sealing elements, Spring elements, Sliding elements, Haptic components, industrial goods, shockproof housing, Gears, Timing belt

Industries:

Automotive, Household appliances, Industry, Agriculture, Mechanical Engineering, Sports & Recreation

Physical properties

Density in kg/m³ | ISO 1183-1	1230

Mechanical properties

Stress at break in MPa | ISO 527-1	47
Strain at break in % | ISO 527-1	380
Impact strength (Charpy) at 23°C in kJ/m² | ISO 179-1eU	N.B.
Notched impact strength (Charpy) at 23°C in kJ/m² | ISO 179-1eA	N.B.
Compression set at 23°C in %. | ISO 815-1	42
Compression set at 70°C in %. | ISO 815-1	56
Shore D hardness | DIN ISO 7619-1	63

Rheological properties

Molding shrinkage in flow direction in % | ISO 294-4	0.65
Molding shrinkage transverse to the flow direction in % | ISO 294-4	0.65

Processing instructions:

Pre-drying recommendation:

Dryer type: dry air dryer
Temperature: 90°C
Drying time: 3 – 4 h
Residual moisture: <0.02

Temperature recommendations:

Melt temperature: 215 – 235°C
Mold temperature: 20 – 50°C

Due to its special properties, KEBAFLEX / U may tend to stick to smooth and polished mold surfaces. Structured surfaces favor the demolding behavior. Alternatively, the mold can be provided with suitable coatings. Please ask our application engineering department for more information.

Post-treatment:

To achieve optimum service properties, the finished parts must be tempered. This heat treatment can be carried out in a forced-air furnace.

Tempering recommendation:

Temperature: 100°C
Tempering time: 20 h

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 22.05.2026

Am Weidenbach 8-10
51491 Overath

Telefon +49 (0)2206 90851-100
Telefax +49 (0)2206 90851-199

E-Mail: kontakt@barlog.de
Web: www.barlog.de