OnFlex™ HT 60A-3S2101

Thermoplastic Elastomer

Key Characteristics

Product Description
OnFlex™ HT thermoplastic elastomer compounds are based on hydrogenated styrenic block copolymers. This range of compounds is specially formulated to deliver very good compression set performance at elevated temperatures and a high heat resistance. Furthermore, OnFlex™ HT compounds are in compliance with EN 681-2 and offer excellent mechanical properties, a wide hardness range and good processability.

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• High Heat Resistance	• Low Compression Set	• Ozone Resistant
Uses	• Pipe Seals		
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Technical Properties [1]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.00 g/cm³	1.00 g/cm³	ISO 1183
Elastomers	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Stress [2]			DIN 53504
Across Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	1520 psi	10.5 MPa	
Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	1150 psi	7.90 MPa	
Tensile Elongation [2]			DIN 53504
Across Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	840 %	840 %	
Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	650 %	650 %	
Tear Strength	183 lbf/in	32.0 kN/m	ISO 34-1
Compression Set			ISO 815
14°F (-10°C), 72 hr	46 %	46 %	
73°F (23°C), 22 hr	24 %	24 %	
158°F (70°C), 22 hr	33 %	33 %	
212°F (100°C), 22 hr	42 %	42 %	
257°F (125°C), 22 hr	43 %	43 %	
302°F (150°C), 22 hr	65 %	65 %	
Stress Relaxation			ISO 3384
73°F (23°C) [3]	31 %	31 %	
73°F (23°C) [4]	13 %	13 %	
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Shore Hardness (Shore A, 10 sec)	60	60	ISO 48-4
IRHD Hardness	70	70	ISO 48

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Aging	Typical Value (English)	Typical Value (SI)	Test Method
Change in Tensile Strength in Air			DIN 53504
158°F (70°C), 168 hr, 0.0787 in (2.00 mm)	-0.50 %	-0.50 %	
Change in Tensile Strain at Break in Air			DIN 53504
158°F (70°C), 168 hr, 0.0787 in (2.00 mm)	-0.90 %	-0.90 %	
Change in Shore Hardness in Air			DIN 53505
Shore A, 158°F (70°C), 168 hr	-3.0	-3.0	
Change in Volume			ISO 1817
158°F (70°C), 72 hr, in ASTM #1 Oil	10 %	10 %	
158°F (70°C), 168 hr, in Water	0.20 %	0.20 %	

Additional Information	Typical Value (English)	Typical Value (SI)
Generic Material Type	Styrenic Thermoplastic Elastomer (TES)	Styrenic Thermoplastic Elastomer (TES)

Properties are measured using injection molded plaques.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	356 to 428 °F	180 to 220 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Fast	Fast

Notes

[1] Typical values are not to be construed as specifications.

[2] 7.9 in/min (200 mm/min)

[3] 100d, 25% compression, Method A

[4] 168hrs, 25% compression, Method A

CONTACT INFORMATION

North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.