Monprene® OM-10152

Teknor Apex Company - Thermoplastic Elastomer

Wednesday, April 1, 2026

General Information

Product Description

Monprene OM-10152 is a specialty thermoplastic elastomer, available in NAT, BLK, and colors, designed for overmolding applications like grips and anti-skid parts for a variety of consumer and industrial products. Monprene OM-10152 is a medium hardness, low density opaque grade that exhibits excellent adhesion to nylon.

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Uses	• Appliances • Bonding • Cell Phones • Flexible Grips	• Handles • Knobs • Overmolding • Power/Other Tools	• Sporting Goods • Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Black	• Colors Available	• Opaque
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.910		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.20	g/10 min	ASTM D1238
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress (300% Strain)	425	psi	ASTM D412
Tensile Strength (Break)	700	psi	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Hardness	**Nominal Value**	**Unit**	**Test Method**
Durometer Hardness			ASTM D2240
Shore A [2]	45		
Shore A [3, 4]	54		
Shore A, 5 sec [3, 4]	52		
Additional Information	**Nominal Value**	**Unit**	
Adhesion to Nylon			

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	150	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	450 to 470	°F
Middle Temperature	480 to 510	°F

Revision Date: 8/18/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Monprene® OM-10152

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Front Temperature	490 to 520	°F
Nozzle Temperature	510 to 530	°F
Processing (Melt) Temp	430 to 470	°F
Mold Temperature	75 to 140	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Fast	
Back Pressure	25.0 to 125	psi
Screw Speed	50 to 120	rpm
Cushion	0.150 to 1.00	in

Notes

[1] Typical properties: these are not to be construed as specifications.

[2] Aged for 0 hr at 72°F

[3] Aged in Air for 48 hr at 72°F

[4] Conditioned for 48 hrs at 22C and 50% RH

Teknor Apex Company
Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan 22
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknoapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 8/18/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector