# Bergaflex™ BFI 60A-363 black SO14 UV

## Thermoplastic Elastomer

## Key Characteristics

| Product Description | | | |
|---|---|---|---|
| Bergaflex™ BFI 60A-363 black SO14 UV is an easy processing, general purpose thermoplastic elastomer based on styrenic block copolymers. This Compound is specially developed to deliver excellent UV stability.<br>Material is highly filled and has therefore a high density. | | | |
| **General** | | | |
| Material Status | • Commercial: Active | | |
| Regional Availability | • Asia Pacific | • Europe | • North America |
| Features | • General Purpose<br>• Good Flow | • Good Processability<br>• UV Resistant | |
| RoHS Compliance | • RoHS Compliant | | |
| Appearance | • Black | | |
| Forms | • Pellets | | |
| Processing Method | • Injection Molding | | |

## Technical Properties [1]

| Physical | Typical Value (English) | Typical Value (SI) | Test Method |
|---|---|---|---|
| Density / Specific Gravity | 1.17 | 1.17 | ISO 1183 |
| **Elastomers** | **Typical Value (English)** | **Typical Value (SI)** | **Test Method** |
| Tensile Stress [2] | | | ISO 37 |
| Break, 73°F (23°C), 0.0787 in (2.00 mm) | 943 psi | 6.50 MPa | |
| Tensile Elongation [2] | | | ISO 37 |
| Break, 73°F (23°C), 0.0787 in (2.00 mm) | 700 % | 700 % | |
| Compression Set | | | ISO 815 |
| 73°F (23°C), 72 hr | 18 % | 18 % | |
| 158°F (70°C), 22 hr | 41 % | 41 % | |
| 212°F (100°C), 22 hr | 80 % | 80 % | |
| **Hardness** | **Typical Value (English)** | **Typical Value (SI)** | **Test Method** |
| Shore Hardness (Shore A, 10 sec) | 60 | 60 | ISO 48-4 |

## Processing Information

| Injection | Typical Value (English) | Typical Value (SI) |
|---|---|---|
| Suggested Max Regrind | 20 % | 20 % |
| Rear Temperature | 329 to 347 °F | 165 to 175 °C |
| Middle Temperature | 347 to 383 °F | 175 to 195 °C |
| Front Temperature | 365 to 437 °F | 185 to 225 °C |
| Nozzle Temperature | 383 to 437 °F | 195 to 225 °C |
| Mold Temperature | 68 to 104 °F | 20 to 40 °C |
| Back Pressure | 290 to 1450 psi | 2.00 to 10.0 MPa |
| Screw Speed | 40 to 100 rpm | 40 to 100 rpm |

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

## Injection Notes

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Bergaflex™ BFI 60A-363 black SO14 UV with minimal property losses, provided that the regrind is free of
contamination. To minimize losses during molding, the melt temperature should be as low as possible. The final determination of regrind
effectiveness should be determined by the customer.

Bergaflex BFI 60A-363 black SO14 UV has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8-10 minutes or longer.

Drying is not Required

## Notes

[1] Typical values are not to be construed as specifications.

[2] 7.9 in/min (200 mm/min)

## CONTACT INFORMATION

**North America**
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

**South America**
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

**Asia**
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

**Europe**
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.