Elexar® EL-1934G AP NAT (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Wednesday, April 1, 2026

General Information

Product Description

Elexar EL-1934G AP is a high performance UL V-0 flame retardant thermoplastic elastomer designed for electrical applications requiring flexibility over a wide temperature range. Elexar EL-1934G AP is a medium hardness, high density grade that is UV stabilized. This UL listed grade is easily colorable and is suitable for both injection molding and extrusion.

General			
Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Filled • Flame Retardant • Good Adhesion • Good Colorability • Good Flexibility	• Good Moldability • Good Processability • Good Toughness • Good Weather Resistance • High Density • High Specific Gravity	• Low Flow • Medium Hardness • Sunlight Resistant (720 hours) • UV Resistant
Uses	• Cable Jacketing • Electrical/Electronic Applications	• Industrial Applications • Insulation	• Wire & Cable Applications • Wire Jacketing
Appearance	• Natural Color	• Opaque	
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.30		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/5.0 kg)	7.0	g/10 min	ASTM D1238
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress (100% Strain)	219	psi	ASTM D412
Tensile Stress (300% Strain)	372	psi	ASTM D412
Tensile Strength (Break)	834	psi	ASTM D412
Tensile Elongation (Break)	550	%	ASTM D412
Hardness	**Nominal Value**	**Unit**	**Test Method**
Durometer Hardness (Shore A)	58		ASTM D2240
Thermal	**Nominal Value**	**Unit**	**Test Method**
Continuous Use Temperature	221	°F	UL 1581
Brittleness Temperature	< -53.0	°F	ASTM D746
RTI Elec	122	°F	UL 746B
RTI Str	122	°F	UL 746B
Aging	**Nominal Value**	**Unit**	**Test Method**
Change in Tensile Strength in Air (277°F, 168 hr)	31	%	ASTM D573
Change in Ultimate Elongation in Air (277°F, 168 hr)	29	%	ASTM D573
Change in Tensile Strength			ASTM D471
140°F, 168 hr, in IRM 902 Oil	-2.3	%	
Change in Ultimate Elongation			ASTM D471
140°F, 168 hr, in IRM 902 Oil	23	%	

Revision Date: 10/7/2021

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Elexar® EL-1934G AP NAT (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (122°F)	3.6E+14	ohms·cm	ASTM D257
Dielectric Strength	1000	V/mil	ASTM D149
Dielectric Constant (1 kHz)	2.64		ASTM D150
Dissipation Factor	5.0E-3		ASTM D150
Flammability	**Nominal Value**	**Unit**	**Test Method**
Flame Rating (0.05 in, All Colors)	V-0		UL 94
Oxygen Index	29	%	ASTM D2863

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	390 to 420	°F
Middle Temperature	415 to 430	°F
Front Temperature	430 to 440	°F
Nozzle Temperature	430 to 445	°F
Processing (Melt) Temp	430 to 445	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	380 to 410	°F
Cylinder Zone 2 Temp.	390 to 420	°F
Cylinder Zone 3 Temp.	415 to 430	°F
Cylinder Zone 4 Temp.	415 to 430	°F
Cylinder Zone 5 Temp.	430 to 440	°F
Die Temperature	430 to 445	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

[1] Typical properties: these are not to be construed as specifications.

Revision Date: 10/7/2021

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Elexar® EL-1934G AP NAT (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Teknor Apex Company
Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan 22
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknoapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 10/7/2021

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector