OnFlex™ HF 9010-70N

Thermoplastic Elastomer

Key Characteristics

Product Description	
OnFlex HF 9010-70N is a thermoplastic elastomer compound based on styrenic block copolymers. It contains a halogen-free flame retardant system. The target hardness is 70 +-5 Sh A.	
General	
Material Status	• Commercial: Active
Regional Availability	• Europe
Uses	• Flame Retardant Jacketing • General Purpose • Gaskets • Industrial Applications
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties [1]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.09 g/cm³	1.09 g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/5.0 kg)	7.0 cm³/10min	7.0 cm³/10min	ISO 1133
Viscosity			Internal Method
GLS method, 200°C, 11170 1/s	13.0 Pa·s	13.0 Pa·s	
GLS method, 200°C, 1340 1/s	60.0 Pa·s	60.0 Pa·s	
Mechanical	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Strength [2]			ISO 37
Flow : 73°F (23°C)	479 psi	3.30 MPa	
Across Flow : 73°F (23°C)	609 psi	4.20 MPa	
Tensile Elongation [2]			ISO 37
Across Flow : Break, 73°F (23°C)	590 %	590 %	
Flow : Break, 73°F (23°C)	300 %	300 %	
Elastomers	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Stress [2]			ISO 37
Across Flow : 100% Strain, 73°F (23°C)	290 psi	2.00 MPa	
Flow : 100% Strain, 73°F (23°C)	406 psi	2.80 MPa	
Tear Strength	148 lbf/in	26.0 kN/m	ISO 34-1
Compression Set (158°F (70°C), 22 hr)	69 %	69 %	ISO 815
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Shore Hardness (Shore A, 10 sec)	70	70	ISO 48-4
Thermal	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Thermal Conductivity (73°F (23°C))	2.7 Btu·in/hr/ft²/°F	0.40 W/m/K	Internal Method
Flammability	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Flame Rating (0.06 in (1.6 mm))	V-0	V-0	UL 94
Glow Wire Flammability Index			IEC 60695-2-12
0.06 in (1.6 mm)	1760 °F	960 °C	

Additional Information
Properties are measured using injection molded plaques.

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 hr	2.0 hr
Processing (Melt) Temp	320 to 356 °F	160 to 180 °C
Mold Temperature	86 to 122 °F	30 to 50 °C

Notes

[1] Typical values are not to be construed as specifications.

[2] 7.9 in/min (200 mm/min)

CONTACT INFORMATION

North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.