PEI-VAT002HFG30
Polyetherimide (PEI)

TECHNICAL DATA SHEET

Description

Sciengy® PEI-VAT002HFG30 is an 30% glass fiber reinforced amorphous polyetherimide (PEI) resin, easy flow with high glass transition temperature (Tg) of 217°C , Provide excellent mechanical, electrical and dimensional properties up to high temperatures.

GF30%, Easy flow, Natural, Black

Series	Glass fiber reinforced
ISO Designation	>PEI-GF30<
Process Method	Injection molding

Properties

Physical	**Value**	**Units**	**Test Standard**
Density	1.50	g/cm³	ISO 1183
Mold Shrinkage	0.3-0.6	%	ISO 2577, 294-4
Melt Flow Rate (337℃. 6.6Kg)	8-15	g/10min	ISO 1133
Water Absorption (24h @23°C)	0.25	%	ISO 62
Mechanical	**Value**	**Units**	**Test Standard**
Tensile Stress at Break (5 mm/min)	170	MPa	ISO 527
Tensile Modulus at Break (1 mm/min)	10	GPa	ISO 527
Elongation at Break (23℃)	2.5	%	ISO 527
Flexural Modulus at Break (23℃)	9.5	GPa	ISO 178
Flexural Strength at Break (23℃)	235	MPa	ISO 178
Notched Izod Impact Strength @23℃ (V-notched)	10	kJ/m²	ISO 180
Thermal	**Value**	**Units**	**Test Standard**
Heat Deflection Temp. High Load (1.8 MPa)	215	°C	ISO 75
Coeff. Of Linear Them. Expansion (parallel)	0.2	E-4/°C	ISO 11359-2
Coeff. Of Linear Them. Expansion (normal)	0.5	E-4/°C	ISO 11359-2
Flammability (0.3 mm)	V-0	Class	UL-94
Flammability (3.0 mm)	V-0	Class	UL-94
Glass Transition (Tg)	217	°C	ISO 11357
Electrical Properties	**Value**	**Units**	**Test Standard**

PEI-VAT002HFG30
Polyetherimide (PEI)

TECHNICAL DATA SHEET

Dielectric Strength (60*60*1mm³)	25	KV/mm	IEC 60243
Relative Permittivity (100Hz&1MHz)	3.5	/	IEC 60250
Dissipation Factor (100Hz&1MHz)	0.0045	/	IEC 60250
Volume Resistivity	10^15	Ω·cm	IEC 60093
Surface Resistivity	10^15	Ω	IEC 60093
CTI	150	V	IEC 60112
Typical Processing Conditions	**Value**	**Units**	**Test Standard**
Drying Temp. / Time	150℃&4~6h	/	/
Injection Speed	Moderate to High	/	/
Injection Molding Melt Temp.	350~400	°C	/
Injection Molding Mold Temp.	140~180	°C	/

Disclaimer

Please refer to Material Safety Data before using this product, The information contained in this data sheet is based on tests of research of Sciengy New Materials Co,.Ltd(Sciengy). The user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the users specific application. Sciengy no warranty is given concerning the accuracy or completeness thereof.