Monprene® SP-29969

Teknor Apex Company - Thermoplastic Elastomer

Friday, April 3, 2026

General Information

Product Description

Monprene SP-29969 is a high performance thermoplastic elastomer that is designed for a variety of consumer applications including sporting goods, and is available in colors. Monprene SP-29969 is a translucent, medium hardness, low density, UV resistant grade that is designed for extrusion and also suitable for injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Abrasion Resistant • Chemical Resistant • Good Adhesion	• Good Colorability • Good Processability • Good Toughness	• Low Density • Medium Hardness • UV Resistant
Uses	• Consumer Applications • Gaskets	• Handles • Sporting Goods	
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color	• Translucent	• White
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.890		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	24	g/10 min	ASTM D1238
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress - Flow (100% Strain)	600	psi	ASTM D412
Tensile Stress - Flow (200% Strain)	650	psi	ASTM D412
Tensile Stress - Flow (300% Strain)	700	psi	ASTM D412
Tensile Strength - Flow (Break)	1540	psi	ASTM D412
Tensile Elongation - Flow (Break)	780	%	ASTM D412
Hardness	**Nominal Value**	**Unit**	**Test Method**
Durometer Hardness			ASTM D2240
Shore A, 1 sec	70		
Shore A, 5 sec	68		

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 450	°F
Middle Temperature	370 to 460	°F
Front Temperature	380 to 470	°F
Nozzle Temperature	390 to 480	°F

Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Monprene® SP-29969

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Processing (Melt) Temp	390 to 480	°F
Mold Temperature	95 to 120	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	360 to 450	°F
Cylinder Zone 2 Temp.	370 to 460	°F
Cylinder Zone 3 Temp.	380 to 470	°F
Cylinder Zone 4 Temp.	390 to 480	°F
Cylinder Zone 5 Temp.	390 to 480	°F
Die Temperature	390 to 480	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

[1] Typical properties: these are not to be construed as specifications.

Teknor Apex Company
Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan 22
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknoapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector