Versaflex™ HC BT218

Thermoplastic Elastomer

Key Characteristics

Product Description

Versaflex™ HC BT218 is a weldable TPE with great tensile strength performance developed for biopharmaceutical tubing applications in healthcare.

- Autoclavable sterilizable
- Weldable
- Kink Resistant

New product. Commercial specifications have not been established.

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Good Color Stability	• Good Flexibility	• Kink Resistant
Uses	• Medical/Healthcare Applications	• Tubing	
Agency Ratings	• ISO 10993-11 • ISO 10993-4	• ISO 10993-5 • USP Class VI [1]	
RoHS Compliance	• RoHS Compliant		
Appearance	• Translucent		
Forms	• Pellets		
Processing Method	• Extrusion		

Technical Properties [2]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.890	0.890	ASTM D792
Elastomers	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Stress [3, 4] (100% Strain, 73°F (23°C))	380 psi	2.62 MPa	ASTM D412
Tensile Stress [3, 4] (300% Strain, 73°F (23°C))	680 psi	4.69 MPa	ASTM D412
Tensile Strength [3, 4] (Break, 73°F (23°C))	1180 psi	8.14 MPa	ASTM D412
Tensile Elongation [3, 4] (Break, 73°F (23°C))	600 %	600 %	ASTM D412
Compression Set			ASTM D395B
72°F (22°C), 22 hr	19 %	19 %	
212°F (100°C), 22 hr	69 %	69 %	
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Durometer Hardness (Shore A, 10 sec)	67	67	ASTM D2240
Fill Analysis	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Apparent Viscosity			ASTM D3835
392°F (200°C), 1340 sec^-1	58.0 Pa·s	58.0 Pa·s	
392°F (200°C), 11200 sec^-1	16.4 Pa·s	16.4 Pa·s	

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	360 to 400 °F	182 to 204 °C
Die Temperature	360 to 420 °F	182 to 216 °C

Extrusion Notes

Rear: 330 to 370F
Center: 350 to 400F
Front: 360 to 420F
Screw speed: 100 to 500 RPM
Drying is not required

Color concentrates with polypropylene (PP), ethylene vinyl acetate (EVA), or low density polyethylene (PE) carriers are most suitable for coloring Versaflex™ HC BT218. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25 - 40g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Liquid color can be used, but mineral oil based carriers may have a significant effect on the final hardness value. Concentrates based on PVC should not be used. A high color match consistency can be obtained by using precolored compounds available from GLS. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

The use of regrind is not recommended for Versaflex™ HC BT218.

Notes

[1] Please contact Avient GLS Thermoplastic Elastomers for a complete copy of the GLS Healthcare Policy.
1. The Customer must notify GLS of any FDA Class I and/or European Union Class I medical devices for each specific product and application.
2. The Customer shall not knowingly manufacture, use, sell or otherwise supply, directly or indirectly products or compounds made from GLS products in any of the following without prior written approval by GLS for each specific product or application:
a. Cosmetics
b. Drugs and other Pharmaceuticals
c. Temporary or permanent implantation in the human body, regardless of the intended duration of implantation
d. Class II and Class III Medical Devices as defined in 21 CFR 860.3 ("Medical Devices")
e. Class IIa, IIb and III as defined in Directive 93/42/EEC

[2] Typical values are not to be construed as specifications.

[3] Die C

[4] 2 hr

CONTACT INFORMATION

North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.