KYNAR FLEX®

TECHNICAL DATA SHEET

KYNAR FLEX® PPA 2200

FLUOROPOLYMERS

The use of Kynar Flex® PPA 2200 resinat 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control

TYPE

PVDF

MAIN APPLICATIONS

- polymer processing aid

DELIVERY FORM

- Pellets

THERMAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	144	°C	ISO 11357-1/-3

OTHER PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Apparent density, 23°C (73°F)	0.7	g/cm³	Internal Arkema

PACKAGING

Available packaging:
- 19 L / 5 gal pail
- 225 kg / 500 lb big bag
- 225 kg / 500 lb metal drum
- 25 kg / 55 lb PE bag
- 25 kg / 55 lb bags
- 3.7 L / 1 gal jug

SPECIAL CHARACTERISTICS

- Flame & smoke

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790
arkema.com

ARKEMA