Wednesday, May 13, 2026

HiFill® PEI GF20

Techmer Polymer Modifiers - *Polyetherimide*

Units SI

Action **Legend (Open)**

General Information

General	
Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.41	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.40	%	ASTM D955
Water Absorption (24 hr)	0.22	%	ASTM D570
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength (Break)	148	MPa	ASTM D638
Flexural Modulus	6550	MPa	ASTM D790
Flexural Strength	217	MPa	ASTM D790
Impact	**Nominal Value**	**Unit**	**Test Method**
Notched Izod Impact (23°C, 3.18 mm)	80	J/m	ASTM D256
Thermal	**Nominal Value**	**Unit**	**Test Method**
Deflection Temperature Under Load (1.8 MPa, Unannealed)	213	°C	ASTM D648
Flammability	**Nominal Value**	**Unit**	**Test Method**
Flame Rating	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	141	°C
Drying Time	3.0	hr
Rear Temperature	357 to 391	°C
Middle Temperature	357 to 391	°C
Front Temperature	357 to 391	°C
Processing (Melt) Temp	354 to 388	°C
Mold Temperature	135 to 163	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	50 to 100	rpm

Notes

[1] Typical properties: these are not to be construed as specifications.

powered by PROSPECTOR®

UL LLC ©2026. All rights reserved.

www.ulprospector.com

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.