TECHNICAL DATASHEET

Grilamid LBV-50H FWA natural

PA12-GF50

EMS-GRIVORY
Material Database

Processing
Injection molding

Delivery form
Granules

Special Characteristics
Light stabilized or stable to light

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Product Information

Product Nomenclature: ISO 16396-PA12,GF50,M1H,C18-120

Mechanical Properties	dry/cond	Unit	Standard
Tensile modulus	13500 / 12500	MPa	ISO 527
Stress at break	170 / 160	MPa	ISO 527
Strain at break	5 / 5	%	ISO 527
Charpy impact strength, +23°C	95 / 90	kJ/m²	ISO 179/1eU
Charpy impact strength, -30°C	95 / 90	kJ/m²	ISO 179/1eU
Charpy notched impact strength, +23°C	18 / 18	kJ/m²	ISO 179/1eA
Charpy notched impact strength, -30°C	14 / 14	kJ/m²	ISO 179/1eA
Ball indentation hardness	- / 190	MPa	ISO 2039-1

Thermal Properties	dry/cond	Unit	Standard
Melting temperature, 10°C/min	178 / -	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	160 / -	°C	ISO 75-1/-2
Temp. of deflection under load, 8.00 MPa	110 / -	°C	ISO 75-1/-2
Max. usage temperature (long term)	90 - 120	°C	ISO 2578
Max. usage temperature (short term)	150	°C	EMS

Electrical Properties	dry/cond	Unit	Standard
Electric strength	- / 40	kV/mm	IEC 60243-1
Comparative tracking index	- / 600		IEC 60112
Volume resistivity	- / 1E10	Ohm*m	IEC 62631-3-1
Surface resistivity	- / 1E11	Ohm	IEC 62631-3-2

General Properties	dry/cond	Unit	Standard
Density	1470 / -	kg/m³	ISO 1183
Burning behav. at thickness h	HB / -	class	IEC 60695-11-10
Thickness tested	0.8 / -	mm	
Water absorption	0.8 / -	%	Sim. to ISO 62

Grilamid LBV-50H FWA natural

General Properties	dry/cond	Unit	Standard
Humidity absorption	0.4 / -	%	Sim. to ISO 62
Molding shrinkage, parallel	0.05 / -	%	ISO 294-4, 2577
Molding shrinkage, normal	0.45 / -	%	ISO 294-4, 2577

Processing Injection Molding	Value	Unit	Standard
Hopper zone	60 - 80	°C	
Feeding zone	250 - 270	°C	
Compression zone	260 - 280	°C	
Metering zone	260 - 280	°C	
Nozzle (IM)	260 - 290	°C	
Melt	270 - 290	°C	
Mold surface temperature	60 - 100	°C	
Injection speed	Medium - High	-	
Pressure	300 - 800	bar	
Dynamic pressure (hydraulic)	50 - 100	bar	
Circumferencial screw speed	5 - 15	m/s	

EMS-CHEMIE AG
Business Unit EMS-GRIVORY

Homepage: EMS-GRIVORY
eMail: welcome@emsgrivory.com

The values are intended to serve as an aid in preselecting materials and for an overview of the EMS-GRIVORY product range. The information contained in this publication is based on our present knowledge and experience. The given figures and data are guidance values and do not represent binding material specifications. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are given regarding products, design, data and information. The customer is not released from his obligation to investigate the products fitness and the suitability for the intended application, compliance with legal requirements and intellectual property rights. We reserve the right to change the information at any time and without prior notice. The information in this publication is not to be considered a contractual obligation and any liability whatsoever is expressly declined. For further questions about our products please contact our experts.

Created: Aug 25, 2026