KYNAR FLEX®

TECHNICAL DATA SHEET

KYNAR FLEX® 3030-15

FLUORINATED COPOLYMER PELLET

KYNAR FLEX® 3030-15 resin is a copolymer of vinylidene fluoride and hexafluoropropylene specifically designed for flexible plenum cables and tubing.

Its main characteristics are:
- Very high flexibility
- High melting point
- Excellent low temperature impact resistance
- Plenum rated

TYPE

PVDF

MAIN APPLICATIONS

- plenum conduit
- plenum cable

DELIVERY FORM

- Pellets

RHEOLOGICAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Melt viscosity, 230°C (446°F) at 100 s-1	7 - 13	kPo	ASTM D3835
Melt flow index (MFR), 230°C / 5 kg (446°F / 11 lb)	8 - 25	g/10min	ASTM D1238

MECHANICAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Tensile modulus, 23°C (73°F)	290	MPa	ASTM D638
Yield stress, 23°C (73°F)	12.4 - 16.5	MPa	ASTM D638
Yield strain, 23°C (73°F)	30	%	ISO 527-1/-2
Stress at break, 23°C (73°F)	19.3 - 24.8	MPa	ASTM D638
Nominal strain at break, 23°C (73°F)	>50	%	ISO 527-1/-2
Flexural modulus, 23°C (73°F)	241 - 379	MPa	ASTM D790
Izod impact notched strength, 23°C (73°F)	No Break		ASTM D256
Charpy notched impact strength, 23°C (73°F)	No Break		ISO 179 1eA
Hardness, shore D	45 - 55		ASTM D2240
Abrasion resistance, wheel CS 17, load 1 kg, 1000 cycles	28 - 33	mg	ASTM G195-13A

KYNAR FLEX® 3030-15

THERMAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Glass transition temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Limiting oxygen index (LOI)	75	%	ASTM D2863
Coefficient of linear thermal expansion, 23°C (73°F)	153 - 194	10E-6 / °K	ASTM D696
Melting temperature, 10°C/min	164	°C	ISO 11357-1/-3

ELECTRICAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Surface resistivity, 23°C (73,4°F)	7.6E+11 - 7.9E+11	ohm/sq	ASTM D257
Dielectric strength, 23°C (73,4°F)	1 - 1.2	kV/mm	ASTM D149

OTHER PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Density, 23°C (73°F)	1.78 - 1.82	g/cm³	ISO 1183-1

PACKAGING

Available packaging:
- 25 kg / 55 lb rigid container
- 680 kg / 1500 lb big bag
- 680 kg /1500 lb rigid container

SPECIAL CHARACTERISTICS

- Flame & smoke

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790
arkema.com