Wednesday, May 13, 2026

HiFill® PVDF White #2 17004058

Techmer Polymer Modifiers - *Polyvinylidene Fluoride*

Units SI

Action **Legend (Open)**

General Information

General	
Material Status	• Commercial: Active
Availability	• North America
Appearance	• White
Processing Method	• Injection Molding

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.75	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	23	g/10 min	ASTM D1238
Moisture (140°C)	0.070	%	
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength (Yield)	48.3	MPa	ASTM D638

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	66	°C
Drying Time	2.0 to 3.0	hr
Rear Temperature	191 to 204	°C
Middle Temperature	193 to 210	°C
Front Temperature	199 to 216	°C
Nozzle Temperature	196 to 216	°C
Processing (Melt) Temp	193 to 216	°C
Mold Temperature	52 to 93	°C
Injection Rate	Slow-Moderate	
Back Pressure	0.00 to 0.345	MPa
Screw Speed	Slow	

Notes

[1] Typical properties: these are not to be construed as specifications.

powered by PROSPECTOR®

UL LLC ©2026. All rights reserved.

www.ulprospector.com

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.