Dynaflex™ G6703-0001

Thermoplastic Elastomer

Key Characteristics

Product Description

Dynaflex™ G6703-0001 is an easy processing compound designed for use in injection molding applications where extremely soft feel properties are desired.

- Excellent Colorability
- Good Ozone Stability
- High Elongation
- Tactile Feel
- Ultra Soft Touch

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Good Colorability	• High Elongation	• Ozone Resistant
Uses	• Consumer Applications • Soft Touch Applications	• Toys • Transparent or Translucent Parts	
Agency Ratings	• FDA		
RoHS Compliance	• RoHS Compliant		
Appearance	• Translucent		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties [1]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.900	0.900	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	4.0 g/10 min	4.0 g/10 min	
200°C/5.0 kg	75 g/10 min	75 g/10 min	
Molding Shrinkage - Flow	0.050 to 0.075 in/in	5.0 to 7.5 %	ASTM D955
Molding Shrinkage - Across Flow	2.0E-3 to 0.030 in/in	0.20 to 3.0 %	ASTM D955
Elastomers	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Stress [2, 3] (100% Strain, 73°F (23°C))	20.0 psi	0.138 MPa	ASTM D412
Tensile Stress [2, 3] (300% Strain, 73°F (23°C))	50.0 psi	0.345 MPa	ASTM D412
Tensile Strength [2, 3] (Break, 73°F (23°C))	550 psi	3.79 MPa	ASTM D412
Tensile Elongation [2, 3] (Break, 73°F (23°C))	1100 %	1100 %	ASTM D412
Tear Strength	40.0 lbf/in	7.01 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	8.0 %	8.0 %	ASTM D395B
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Durometer Hardness (Shore A, 10 sec)	3	3	ASTM D2240
Fill Analysis	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec^-1	5.20 Pa·s	5.20 Pa·s	

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	290 to 340 °F	143 to 171 °C
Middle Temperature	300 to 350 °F	149 to 177 °C
Front Temperature	350 to 370 °F	177 to 188 °C
Nozzle Temperature	350 to 440 °F	177 to 227 °C
Mold Temperature	60 to 80 °F	16 to 27 °C
Back Pressure	0.00 to 110 psi	0.00 to 0.758 MPa
Screw Speed	40 to 100 rpm	40 to 100 rpm

Injection Notes

Color concentrates with polypropylene (PP), ethylene vinyl acetate (EVA), or low density polyethylene (PE) carriers are most suitable for coloring Dynaflex™ G6703-1000. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25 - 40 g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Liquid color can be used, however mineral oil based carriers may have a significant effect on the final hardness value. Concentrates based on PVC should not be used. A high color match consistency can be obtained by using precolored compounds available from GLS. The final determination of color concentrate suitability should be should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Dynaflex™ G6703-0001 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Dynaflex™ G6703-0001 has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

Injection Speed: 1 to 3 in/sec
1st Stage - Boost Pressure: 125 to 700 psi
2nd Stage - Hold Pressure: 30% of Boost
Hold Time (Thick Part): 3 to 10 sec
Hold Time (Thin Part): 1 to 3 sec

Notes

[1] Typical values are not to be construed as specifications.

[2] Die C

[3] 2 hr

CONTACT INFORMATION

North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.