Versollan™ RU 2205-9

Thermoplastic Elastomer

Key Characteristics

Product Description

Versollan™ RU 2205-9 is a high performance, injection moldable TPU alloy developed to offer a rubbery feel and appearance, reduced cycle times, and performance properties associated with TPUs.

- Bonds to PC, ABS, PC/ABS, and Copolyester
- Excellent Abrasion Resistance
- Fast Set Up Rates During Processing
- Matte Finish
- Rubbery, Soft Touch Feel
- Very Good Oil Resistance

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Abrasion Resistant	• Oil Resistant	
Uses	• Consumer Applications • Furniture	• Overmolding • Power/Other Tools	• Soft Touch Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Technical Properties [1]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.16	1.16	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	7.0 g/10 min	7.0 g/10 min	
200°C/5.0 kg	67 g/10 min	67 g/10 min	
Molding Shrinkage - Flow	0.010 to 0.015 in/in	1.0 to 1.5 %	ASTM D955
Elastomers	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Stress [2, 3] (100% Strain, 73°F (23°C))	380 psi	2.62 MPa	ASTM D412
Tensile Stress [2, 3] (300% Strain, 73°F (23°C))	610 psi	4.21 MPa	ASTM D412
Tensile Strength [2, 3] (Break, 73°F (23°C))	2000 psi	13.8 MPa	ASTM D412
Tensile Elongation [2, 3] (Break, 73°F (23°C))	710 %	710 %	ASTM D412
Tear Strength	270 lbf/in	47.3 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	34 %	34 %	ASTM D395B
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Durometer Hardness (Shore A, 10 sec)	65	65	ASTM D2240
Thermal	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Brittleness Temperature [4]	-88.6 °F	-67.0 °C	ASTM D746
Fill Analysis	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec^-1	14.1 Pa·s	14.1 Pa·s	

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	125 to 130 °F	52 to 54 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	< 0.030 %	< 0.030 %
Suggested Max Regrind	20 %	20 %
Rear Temperature	335 to 370 °F	168 to 188 °C
Middle Temperature	355 to 390 °F	179 to 199 °C
Front Temperature	375 to 410 °F	191 to 210 °C
Nozzle Temperature	375 to 420 °F	191 to 216 °C
Processing (Melt) Temp	370 to 410 °F	188 to 210 °C
Mold Temperature	70 to 90 °F	21 to 32 °C
Back Pressure	0.00 to 125 psi	0.00 to 0.862 MPa
Screw Speed	75 to 125 rpm	75 to 125 rpm

Injection Notes

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Versollan™ RU 2205-9 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Versollan™ RU 2205-9 should not be left in the barrel for extended idle periods (greater than 5 minutes).

Suggested Dewpoint: -40°F

Injection Speed: 0.5 to 2 in/sec
1st Stage - Boost Pressure: 300 to 700 psi
2nd Stage - Hold Pressure: 30% of Boost
Hold Time (Thick Part): 4 to 10 sec
Hold Time (Thin Part): 1 to 3 sec

Notes

[1] Typical values are not to be construed as specifications.

[2] Die C

[3] 2 hr

[4] Thickness = 1.91mm
Conditioned for 40hrs at 23C at 50% RH

CONTACT INFORMATION

North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.