Monprene® OM-12265 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Wednesday, April 1, 2026

General Information

Product Description

Monprene OM-12265 is a specialty thermoplastic elastomer designed for overmolding and co-extrusion applications like grips and anti-skid parts for consumer and industrial products. Monprene OM-12265 is a medium hardness, medium density, RoHS compliant grade that exhibits excellent adhesion to PC, ABS, PC/ABS, & PP.

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Abrasion Resistant • Bondability • Chemical Resistant • Chemically Coupled • Conformable • Crack Resistant	• Creep Resistant • Ductile • Good Color Stability • Good Flexibility • Good Flow • Good Moldability	• Good Processability • Lubricated • Medium Density • Medium Hardness • Without Fillers
Uses	• Appliances • Bonding • Cell Phones • Consumer Applications	• Flexible Grips • Handles • Knobs • Overmolding	• Power/Other Tools • Soft Touch Applications • Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.960		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress (300% Strain)	650	psi	ASTM D412
Tensile Strength (Break)	1300	psi	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Hardness	**Nominal Value**	**Unit**	**Test Method**
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	68		
Shore A, 5 sec, Injection Molded	66		
Flammability	**Nominal Value**	**Unit**	**Test Method**
Flame Rating			UL 94
0.12 in, All Colors	HB		
0.24 in, All Colors	HB		
Additional Information	**Nominal Value**	**Unit**	
Adhesion to ABS			
Adhesion to PC			
Adhesion to PC/ABS			

Revision Date: 1/24/2025

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Monprene® OM-12265 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	140	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	280 to 320	°F
Middle Temperature	360 to 390	°F
Front Temperature	360 to 390	°F
Nozzle Temperature	380 to 410	°F
Processing (Melt) Temp	350 to 390	°F
Mold Temperature	40 to 120	°F
Injection Pressure	200 to 800	psi
Back Pressure	25.0 to 125	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Moisture can degrade the material. Drying is suggested. This can be accomplished by placing the material in a desiccant dryer for 2 to 4 hours at 140°F.

For any overmolding process it is recommended that the process temperatures for the TPE material be set at least 50°F (10°C)higher than the melt temperature of the substrate material.

Notes

[1] Typical properties: these are not to be construed as specifications.

Teknor Apex Company
Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan 22
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknoapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 1/24/2025

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector