TECHNICAL DATASHEET

TRIEL® 5063SPU

TPEE

PROPERTY	UNIT	ASTM METHOD	TYPICAL DATA
PHYSICAL			
Specific Gravity	-	D792	1.10
Water Absorption (24 hours at 23℃)	%	D570	0.5
Melt Flow Rate (230도, 2.16kg)	g/10min	D1238	8
MECHANICAL			
Tensile Strength at yield	$kg_f/㎠$	D638	80
Tensile Elongation at break	%	D638	>400
Flexural Strength at yield	$kg_f/㎠$	D790	20
Flexural Modulus	$kg_f/㎠$	D790	100
Izod Impact Strength, notched, 23℃ (1/8")	$kg_f·㎝/㎝$	D256	No Break
Hardness (Shore D)	Shore D		70~75A
THERMAL			
ELECTRICAL			
OTHERS			
Mold Shrinkage	%		1.5~1.7

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

PROCESSING GUIDE

TRIEL® 5063SPU GRADE

TPEE

- General processing conditions for TRIEL5063SPU are shown below. Drying prior to processing is essential to ensure desired appearance and property performance.

SPECIFICATION	UNIT	CONDITIONS
Drying Temperature	℃	90~100
Drying Time	hr	3~4
Moisture Content, Max	%	0.02
Melt Temperature	℃	180~190
Nozzle Temperature	℃	190~230
Front Temperature	℃	190~220
Middle Temperature	℃	190~220
Rear Temperature	℃	190~210
Mold Temperature	℃	40~60
Back Pressure	MPa	0.0~0.1
Screw Speed	rpm	10~50
Vent Depth	mm	0.02~0.08

Global Network

HEAD OFFICE
Samyang Corporation
31, Jong-ro 33-gil, Jongno-gu, Seoul, Korea
T. +82-2-740-7747

Chemical Research Center
730, Daedeok-daero, Yuseong-gu, Daejeon, Korea
T. +82-42-865-8114

JEONJU ENGINEERING PLASTIC PLANT
147, Palbok-ro, Deokjin-gu, Jeonju, Korea
T. +82-63-210-6664

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.
No.131, Shuangying Road, Qingpu Industrial Area,
Qingpu County, Shanghai, China
T. +86-21-6922-2270

SAMYANG ENGINEERING PLASTICS (HUNGARY) CO., LTD.
H5100, Jaszbereny, Necso, Telep 1, Hungary
T. +36-21-311-1263

SAMYANG ENGINEERING PLASTICS (VIETNAM) LLC
1 Song Hanh Road, Nhon Trach 6 Industrial Zone, Long Tho
Commune, Nhon Trach District, Dong Nai Province, Vietnam
T. +84-0251-3686-707