Preliminary ENSOFT SL-154-45A

ENSOFT-S

Product Description : This polyolefin based thermoplastic elastomer (SEBS) compound is high mineral filled, completely recyclable and possible alternative to replace PVC in various applications. ENSOFT® series can be processed with conventional thermoplastics machinery

Additive Packages : T / Heat and UV stabilizer
/

Key Features : Good ozone and UV resistance
Easy processing
Rubberlike elasticity
Easy colorability with proper MB (PE, PP, etc. based).

Process Method : Extrusion, coextrusion, sheet extrusion

Uses : Extruded parts (seals, tubes, profiles, hoses, etc.) for construction and furniture

Revision Date : 01.12.2018

	Value	Unit	Standard
Physical			
Hardness	45	SHORE A	ISO 868 (3 second)
Density	1,17	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	1	Mpa	ISO 37, DIN 53504
300% Modulus	1,5	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	3,4	Mpa	ISO 37, DIN 53504
Elongation at Break	>400	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	17	N/mm	ISO 34-1
Aging			
Compression Set (72h/23°C)	22	%	ISO 815
Thermal			
Max. Dynamic Service Temperature	90	°C	*
Max. Static Service Temperature	110	°C	*

Environmental Resistance	
Ozone	Excellent

Data Sheet

Ravago Petrokimya Uretim A.S.

Main Office : *Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey* ***Tel :*** *+90 850 314 70 99*

Plant : *Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey* ***Fax :*** *+90 262 672 10 51*

Mail / Web : *info@ravagopetrokimya.com.tr* *www.ravagopetrokimya.com.tr*

Preliminary ENSOFT SL-154-45A

ENSOFT-S

Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good
Drying Condition	
Drying Time(hr)	Not required
Drying Temperature(°C)	Not required
Extrusion Condition (°C)	
Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

Important Notice;

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.

Ravago Petrokimya Uretim A.S.

Main Office : *Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey* ***Tel :*** *+90 850 314 70 99*

Plant : *Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey* ***Fax :*** *+90 262 672 10 51*

Mail / Web : *info@ravagopetrokimya.com.tr* *www.ravagopetrokimya.com.tr*