WDF® PA12 120-TR NC

Polyamide 12

Worldful Polymer (Shanghai) Co., Ltd.

PROSPECTOR®
www.ulprospector.com

Technical Data

Product Description	
120-TR is a transparent flexible PA12 material, the material has excellent mechanical properties, excellent low temperature toughness, high transparency, yellowing resistance, hydrolysis resistance.	

General		
Material Status	• Commercial: Active	
Literature [1]	• Technical Datasheet (Chinese) • Technical Datasheet (English)	
Availability	• Asia Pacific	
Features	• Good Flexibility • Good Thermal Stability	• Hydrolysis Resistant • Low Temperature Toughness
Uses	• Appliances	• Industrial Applications
Appearance	• Clear/Transparent	• Natural Color
Processing Method	• Injection Molding	

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.01	g/cm³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.40 to 0.70	%	
Across Flow	0.60 to 0.90	%	
Water Absorption (Equilibrium)	0.70	%	ASTM D570
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength [3]	60.0	MPa	ASTM D638
Tensile Elongation [3] (Break)	> 50	%	ASTM D638
Flexural Modulus [4]	1400	MPa	ASTM D790
Impact	**Nominal Value**	**Unit**	**Test Method**
Charpy Unnotched Impact Strength	No Break		ASTM D256
Notched Izod Impact	130	J/m	ASTM D256
Thermal	**Nominal Value**	**Unit**	**Test Method**
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	135	°C	
1.8 MPa, Unannealed	115	°C	
Melting Temperature	178	°C	ASTM D2133
Electrical	**Nominal Value**	**Unit**	**Test Method**
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Electric Strength	34	kV/mm	IEC 60243-1
Comparative Tracking Index	600	V	IEC 60112
Flammability	**Nominal Value**	**Unit**	**Test Method**
Flame Rating			UL 94
1.6 mm	HB		
3.2 mm	HB		

Injection	Nominal Value	Unit
Drying Temperature	80 to 100	°C
Drying Time	4.0 to 6.0	hr
Rear Temperature	210 to 230	°C
Middle Temperature	230 to 250	°C
Front Temperature	220 to 240	°C
Processing (Melt) Temp	210 to 230	°C
Mold Temperature	60 to 80	°C
Injection Rate	Slow-Moderate	
Back Pressure	2.00 to 4.00	MPa

Form No. TDS-403578-en

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.
UL Prospector | 800-788-4668 or 307-742-9227 | www.ulprospector.com.

Document Created: Thursday, April 18, 2019
Added to Prospector: April 2018
Last Updated: 4/20/2018

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Injection Notes

Processing Temp. Limit <260 °C

Notes

[1] These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

[2] Typical properties: these are not to be construed as specifications.

[3] 50 mm/min

[4] 20 mm/min

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.
UL Prospector | 800-788-4668 or 307-742-9227 | www.ulprospector.com.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Form No. TDS-403578-en
Document Created: Thursday, April 18, 2019
Added to Prospector: April 2018
Last Updated: 4/20/2018

Where to Buy

Supplier

Worldful Polymer (Shanghai) Co., Ltd.
Shanghai, China
Telephone: +86-21-51688081
Web: http://www.wdfsh.cn

Distributor

Worldful Polymer (Shanghai) Co., Ltd.
Telephone: +86-21-51688081; Mr. Ma Cell: +86-13621999631
Web: http://www.wdfsh.cn
Availability: China

Form No. TDS-403578-en

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.
UL Prospector | 800-788-4668 or 307-742-9227 | www.ulprospector.com.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Document Created: Thursday, April 18, 2019
Added to Prospector: April 2018
Last Updated: 4/20/2018