OnFlex™ BIO 5370A-E0004

Thermoplastic Elastomer

Key Characteristics

Product Description

OnFlex™-Bio 5300 series thermoplastic elastomer compounds are soft thermoplastic polyurethane compounds made from renewable natural sources. These compounds contain at least 20% of renewable material as certified according to ASTM-D6866. The OnFlex™-Bio 5300 series compounds are formulated to provide an excellent surface finish, soft-touch haptic, abrasion resistance and mechanical properties.

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Abrasion Resistant	• Good Scratch Resistance	• Renewable Resource Content
Uses	• Automotive Applications	• Consumer Applications	• General Purpose
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Calendering • Extrusion	• Injection Molding • Multi Injection Molding	

Technical Properties [1]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.05 g/cm³	1.05 g/cm³	ISO 1183
Mechanical	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Abrasion Loss	63.0 mm³	63.0 mm³	DIN 53516
Elastomers	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Stress [2]			DIN 53504
Across Flow : 100% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	479 psi	3.30 MPa	
Flow : 100% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	551 psi	3.80 MPa	
Tensile Stress [2]			DIN 53504
Across Flow : 300% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	1150 psi	7.90 MPa	
Flow : 300% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	1330 psi	9.20 MPa	
Tensile Stress [2]			DIN 53504
Across Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	1600 psi	11.0 MPa	
Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	1840 psi	12.7 MPa	
Tensile Elongation [2]			DIN 53504
Across Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	410 %	410 %	
Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	410 %	410 %	

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tear Strength [3]			ISO 34-1
Across Flow : 73°F (23°C), 0.0787 in (2.00 mm)	245 lbf/in	42.9 kN/m	
Flow : 73°F (23°C), 0.0787 in (2.00 mm)	270 lbf/in	47.2 kN/m	
Compression Set			ISO 815
73°F (23°C), 72 hr	51 %	51 %	
158°F (70°C), 22 hr	73 %	73 %	
212°F (100°C), 22 hr	84 %	84 %	
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Shore Hardness (Shore A, 10 sec)	70	70	ISO 48-4
Additional Information	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Odor Rating [4]	3.0	3.0	VDA 270

Properties are measured using injection molded plaques.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	212 to 248 °F	100 to 120 °C
Drying Time	1.0 to 2.0 hr	1.0 to 2.0 hr
Processing (Melt) Temp	356 to 428 °F	180 to 220 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Fast	Fast

Notes

[1] Typical values are not to be construed as specifications.

[2] Type 1, 7.9 in/min (200 mm/min)

[3] Method A, Trouser

[4] Method A3

CONTACT INFORMATION

North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.