Monprene® OM-16245

Teknor Apex Company - Thermoplastic Elastomer

Thursday, April 2, 2026

General Information

Product Description

Monprene OM-16245 is specialty thermoplastic elastomer designed for overmolding and co-extrusion applications like grips and anti-skid parts for consumer and industrial products. Monprene OM-16245 is a medium hardness RoHS compliant grade that exhibits excellent adhesion to PC, ABS and PC/ABS.

General			
Material Status	• Commercial: Active		
Availability	• Asia Pacific		
Uses	• Appliances • Bonding • Cell Phones • Dental Applications	• Flexible Grips • Handles • Knobs • Overmolding	• Power/Other Tools • Sporting Goods • Toothbrush Handles • Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.00		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	10	g/10 min	ASTM D1238
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress (100% Strain)	174	psi	ASTM D412
Tensile Stress (300% Strain)	348	psi	ASTM D412
Tensile Strength (Break)	580	psi	ASTM D412
Tensile Elongation (Break)	500	%	ASTM D412
Compression Set (73°F, 22 hr)	20	%	ASTM D395
Hardness	**Nominal Value**	**Unit**	**Test Method**
Durometer Hardness			ASTM D2240
Shore A	48		
Shore A, 5 sec	46		
Thermal	**Nominal Value**	**Unit**	**Test Method**
RTI Elec	122	°F	UL 746B
RTI Imp	122	°F	UL 746B
RTI Str	122	°F	UL 746B
Flammability	**Nominal Value**	**Unit**	**Test Method**
Flame Rating (0.04 to 0.05 in, All Colors)	HB		UL 94
Additional Information	**Nominal Value**	**Unit**	
Adhesion to ABS			
Adhesion to PC			
Adhesion to PC/ABS			

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	140	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	284 to 356	°F

Revision Date: 9/22/2021

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Monprene® OM-16245

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Middle Temperature	320 to 410	°F
Front Temperature	338 to 410	°F
Nozzle Temperature	338 to 419	°F
Processing (Melt) Temp	338 to 419	°F
Mold Temperature	40 to 140	°F
Injection Pressure	200 to 800	psi
Back Pressure	25.0 to 125	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Moisture can degrade the material. Drying is suggested. This can be accomplished by placing the material in a desiccant dryer for 2 to 4 hours at 60°C/140°F.

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	280 to 300	°F
Cylinder Zone 2 Temp.	300 to 320	°F
Cylinder Zone 3 Temp.	320 to 360	°F
Cylinder Zone 5 Temp.	340 to 380	°F
Die Temperature	360 to 400	°F

Notes

[1] Typical properties: these are not to be construed as specifications.

Teknor Apex Company
Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan 22
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknoapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 9/22/2021

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector