Wednesday, May 13, 2026

HiFill® PPSU A1 0200 B LE

Techmer Polymer Modifiers - *Polyphenylsulfone*

Units SI

Action **Legend (Open)**

General Information

General		
Material Status	• Commercial: Active	
Availability	• North America	
Features	• High Density	• Low Extractables
Agency Ratings	• FDA	
Appearance	• Colors Available	• Opaque
Forms	• Pellets	
Processing Method	• Injection Molding	

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	2.00	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.50	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength (Yield)	62.1	MPa	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	3030	MPa	ASTM D790
Flexural Strength	109	MPa	ASTM D790
Impact	**Nominal Value**	**Unit**	**Test Method**
Notched Izod Impact (3.18 mm)	64	J/m	ASTM D256
Hardness	**Nominal Value**	**Unit**	**Test Method**
Rockwell Hardness (R-Scale)	120		ASTM D785
Thermal	**Nominal Value**	**Unit**	**Test Method**
Deflection Temperature Under Load (0.45 MPa, Unannealed)	220	°C	ASTM D648
Deflection Temperature Under Load (1.8 MPa, Unannealed)	209	°C	ASTM D648
CLTE - Flow	7.2E-5	cm/cm/°C	ASTM D696
Electrical	**Nominal Value**	**Unit**	**Test Method**
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	19	kV/mm	ASTM D149
Flammability	**Nominal Value**	**Unit**	**Test Method**
Flame Rating (3.0 mm)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	160	°C
Drying Time	3.0	hr
Rear Temperature	357 to 391	°C
Middle Temperature	357 to 391	°C
Front Temperature	357 to 391	°C
Processing (Melt) Temp	343 to 399	°C
Mold Temperature	110 to 149	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	50 to 100	rpm

Notes

[1] Typical properties: these are not to be construed as specifications.

powered by PROSPECTOR® UL LLC ©2026. All rights reserved.

www.ulprospector.com

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.