# Versaflex™ CF 5701 N

## Thermoplastic Elastomer

### Key Characteristics

| Product Description |
|---|
| Versaflex™ CF 5701 N is a compound designed for the adhesive layer of protective films with features of low oil bleeding, low residues and high tack. |

| General | | |
|---|---|---|
| Material Status | • Commercial: Active | |
| Regional Availability | • Africa & Middle East<br>• Asia Pacific | • Europe<br>• Latin America |
| RoHS Compliance | • RoHS Compliant | |
| Appearance | • Translucent | |
| Forms | • Pellets | |
| Processing Method | • Extrusion | |

### Technical Properties [1]

| Physical | Typical Value (English) | Typical Value (SI) | Test Method |
|---|---|---|---|
| Density / Specific Gravity | 0.930 | 0.930 | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 kg) | 7.0 g/10 min | 7.0 g/10 min | ASTM D1238 |
| **Hardness** | **Typical Value (English)** | **Typical Value (SI)** | **Test Method** |
| Durometer Hardness [2] | | | ASTM D2240 |
| Shore A, 10 sec, 73°F (23°C) | 28 | 28 | |
| **Fill Analysis** | **Typical Value (English)** | **Typical Value (SI)** | **Test Method** |
| Apparent Viscosity | | | ASTM D3835 |
| 392°F (200°C), 11200 sec^-1 | 16.7 Pa·s | 16.7 Pa·s | |

### Processing Information

| Extrusion | Typical Value (English) | Typical Value (SI) |
|---|---|---|
| Melt Temperature | 375 to 460 °F | 191 to 238 °C |
| Die Temperature | 375 to 460 °F | 191 to 238 °C |

| Extrusion Notes |
|---|
| Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).<br><br>Drying is not Required.<br><br>Screw Speed = 100-700 RPM |

**Notes**

[1] Typical values are not to be construed as specifications.

[2] 2 hr

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

## CONTACT INFORMATION


### North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

### South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

### Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

### Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com


Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.