Versaflex™ CE 3130-70N

Thermoplastic Elastomer

Key Characteristics

Product Description			
Versaflex™ CE 3130-70N is targeted for consumer electronics applications where excellent surface appearance with long-term life, excellent abrasion resistance, performed UV and stain resistance, chemical resistance and silky feel are required. Versaflex™ CE 3130-70N can also overmold to a variety of substrates including PC, ABS, PC/ABS, and Copolyester.			
General			
Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific	• Europe	• North America
Features	• Good Colorability • Good Processability	• Low Friction • Pleasing Surface Appearance	
Uses	• Consumer Applications	• Electrical/Electronic Applications	• Overmolding
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties [1]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.04	1.04	ASTM D792
Molding Shrinkage - Flow	2.0E-3 to 8.0E-3 in/in	0.20 to 0.80 %	ASTM D955
Elastomers	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Stress (300% Strain)	856 psi	5.90 MPa	ASTM D412
Tensile Strength [2, 3] (Break, 73°F (23°C))	2220 psi	15.3 MPa	ASTM D412
Tensile Elongation [2, 3] (Break, 73°F (23°C))	660 %	660 %	ASTM D412
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Durometer Hardness (Shore A, 10 sec)	70	70	ASTM D2240
Fill Analysis	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec^-1	22.2 Pa·s	22.2 Pa·s	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	158 to 176 °F	70 to 80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.020 to 0.030 %	0.020 to 0.030 %
Suggested Max Regrind	20 %	20 %
Rear Temperature	340 to 360 °F	171 to 182 °C
Middle Temperature	360 to 430 °F	182 to 221 °C
Front Temperature	370 to 440 °F	188 to 227 °C
Nozzle Temperature	380 to 460 °F	193 to 238 °C
Processing (Melt) Temp	380 to 450 °F	193 to 232 °C
Mold Temperature	55 to 110 °F	13 to 43 °C
Back Pressure	0.00 to 50.0 psi	0.00 to 0.345 MPa

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Injection	Typical Value (English)	Typical Value (SI)
Screw Speed	50 to 100 rpm	50 to 100 rpm

Injection Notes

Color concentrates with EVA or TPU carriers are most suitable for coloring Versaflex CE 3130-70N. Typical letdown ratios are 50:1 to 25:1 - loading levels should be as low as possible to minimize the effect on adhesion. A high color match consistency can be obtained by the use of precolored compounds available from GLS. Concentrates based on PVC should not be used. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Versaflex CE 3130-70N with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Versaflex CE 3130-70N should not be left in the barrel for extended idle periods (greater than 5 minutes).

Suggested Dewpoint: -40°F

Injection Speed: 0.5 to 4 in/sec
1st Stage - Boost Pressure: 500 to 1,000 psi
2nd Stage - Hold Pressure: 20-60% of Boost
Hold Time (Thick Part): 2 to 4 sec
Hold Time (Thin Part): 1 to 2 sec

Notes

[1] Typical values are not to be construed as specifications.

[2] Die C

[3] 2 hr

CONTACT INFORMATION

North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.