KYNAR®

TECHNICAL DATA SHEET

KYNAR® POWERFLEX LBG

FLUORINATED COPOLYMER POWDER

Kynar® Powerflex LBG is a fluorinated copolymer designed for lithium battery separator coating. It can be used either in solvent-based processes or water-based (powder redispersion) processes.

TYPE

PVDF

MAIN APPLICATIONS

- battery

DELIVERY FORM

- Powder

RHEOLOGICAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Melt viscosity, 230°C (446°F) at 100 s-1	36	kPo	ASTM D3835

THERMAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	153	°C	ASTM D3418

OTHER PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Metal content, metals (Cr, Fe, Co, Ni, Cu, Zn)	< 5 each	ppm	Internal Arkema
Particle Size Distribution (PSD), median particles size (D50)	10	µm	GB/T 19077
Density, 23°C (73°F)	1.78	g/cm³	ISO 1183-1

PACKAGING

Available packaging:
- 20 kg / 44 lb boxes

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

HPP - 2026-07-10 - Page: 1 / 1

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790
arkema.com

ARKEMA