Wednesday, May 13, 2026

HiFill® PPSU 5500 BSF06 LE GY061

Techmer Polymer Modifiers - *Polyphenylsulfone*

Units English

Action **Legend (Open)**

General Information

General	
Material Status	• Commercial: Active
Availability	• North America
Features	• Low Extractables
Appearance	• Grey
Processing Method	• Injection Molding

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.36		ASTM D792
Melt Mass-Flow Rate (MFR) (365°C/5.0 kg)	15	g/10 min	ASTM D1238
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength (Yield)	9900	psi	ASTM D638
Tensile Strength (Break)	8400	psi	ASTM D638
Tensile Elongation (Break)	54	%	ASTM D638
Impact	**Nominal Value**	**Unit**	**Test Method**
Notched Izod Impact (0.125 in)	4.3	ft·lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	300	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	640 to 730	°F
Middle Temperature	640 to 730	°F
Front Temperature	640 to 730	°F
Nozzle Temperature	640 to 730	°F
Processing (Melt) Temp	680 to 735	°F
Mold Temperature	280 to 325	°F
Injection Rate	Slow	
Back Pressure	0.00 to 100	psi
Screw Speed	Slow-Moderate	

Notes

[1] Typical properties: these are not to be construed as specifications.

powered by PROSPECTOR®

UL LLC ©2026. All rights reserved.

www.ulprospector.com

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.