Ajedium™ Films -- PPSU
polyphenylsulfone

PPSU polyphenylsulfone is an amorphous thermoplastic material that offers exceptional hydrolytic stability, and toughness superior to other commercially available, high-temperature flims.

PPSU films have high deflection temperatures and outstanding resistance to environmental stress cracking. The polymer is inherently flame retardant.

The excellent thermal stability makes films suitable for applications where very low shrink at high temperatures are needed. PPSU films also have good electrical properties.

PPSU film is off-white in color.

General		
Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Features	• Flame Retardant • Good Electrical Properties • Good Thermal Stability	• Good Toughness • High ESCR (Stress Crack Resist.) • Hydrolytically Stable
Uses	• Aerospace Applications • Aircraft Applications • Automotive Applications • Batteries	• Electrical/Electronic Applications • Food Service Applications • Medical/Healthcare Applications
RoHS Compliance	• Contact Manufacturer	
Appearance	• Off-White	

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.30		ASTM D792
Water Absorption (24 hr)	0.37	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tear Resistance - (25 µm)	1.79	lbf	ASTM D1004

Films	Typical Value	Unit	Test method
Film Thickness - Tested			
--	25	µm	
--[1]	50	µm	
--[2]	130	µm	
Secant Modulus			ASTM D882
MD	1590	MPa	
TD	1980	MPa	

Ajedium™ Films -- PPSU
polyphenylsulfone

Films	Typical Value	Unit	Test method
Tensile Strength			ASTM D882
MD : Yield	68.0	MPa	
TD : Yield	59.0	MPa	
MD : Break	92.0	MPa	
TD : Break	70.0	MPa	
Tensile Elongation			ASTM D882
MD : Yield	9.2	%	
TD : Yield	6.8	%	
MD : Break	140	%	
TD : Break	100	%	
Dart Drop Impact	750	g	ASTM D1709B
Area Factor	149	ft²/lb/mil	
Tear Propagation Resistance	140	gf	ASTM D1922
Water Vapor Transmission Rate	276	g/m²/bar/24 hr	ASTM F1249

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed, 3.18 mm	207	°C	
Glass Transition Temperature	220	°C	ASTM E1356
CLTE - Flow (3.18 mm)	5.6E-5	cm/cm/°C	ASTM D696
Specific Heat - (23°C)	614	J/kg/°C	ASTM D3418

Electrical	Typical Value	Unit	Test method
Volume Resistivity	9.0E+15	ohms·cm	ASTM D257
Dielectric Strength (0.0250 mm)	190	kV/mm	ASTM D149
Dielectric Constant	3.45		ASTM D150

Flammability	Typical Value	Unit	Test method
Oxygen Index	38	%	ASTM D2863

Ajedium™ Films -- PPSU
polyphenylsulfone

Additional Information

Standard Thicknesses and Widths

- Widths are available from 22" (559 mm) to 56" (1422 mm).
- Products with widths <22 inches or >56 inches are available upon request.
- Tolerances for widths are +/- 4mm.
- For PPSU film, the standard thicknesses are 25 microns (1 mil) to 1016 microns (40 mil).

Surface Finishes

- Standard surface finish is P/M (polished / matte).
- Custom finishes of P/P (polished / polished) and M/M (matte / matte) are available.

Packaging

- Film is supplied in a roll form of high quality, cardboard core of 3" (76mm) or 6" (152mm).
- PVC cores are available upon request in 3" and 6" sizes.

Labeling

- Products are labeled to comply with national and international standards.
- Labels include product grade, unique batch number, roll length, roll width, product thickness, and net weight.

Notes

Typical properties: these are not to be construed as specifications.

[1] Impact Properties

[2] Tear Properties

www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2026 2023 Syensqo. All rights reserved.