Monprene® R2 CP-15155 NAT XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Thursday, April 2, 2026

General Information

Product Description

The Monprene® RX CP-15100 series of thermoplastic elastomers (TPEs) is formulated to contain post-consumer recycled (PCR) content, reducing dependency on virgin petroleum-based plastic and contributing towards a circular economy. These high-flow materials, designed for injection molding or overmolding onto polypropylene, perform and process like prime TPE, and are available in a light, natural color. Monprene R2 CP-15155 is a 55 Shore A TPE containing 25% PCR content and is available globally with locally sourced raw materials.

General			
Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Recycled Content	• Post-Consumer (PCR), 25%		
Features	• Chemical Resistant • Good Adhesion • Good Colorability • Good Flexibility • Good Moldability	• Good Processability • Good Toughness • Halogen Free • High Elongation • High Flow	• High Tensile Strength • Low Compression Set • Low Density • Medium Hardness • Resilient
Uses	• Consumer Applications • Flexible Grips • General Purpose • Handles	• Knobs • Lawn & Garden Equipment • Luggage • Overmolding	• Rubber Replacement • Soft Touch Applications • Sporting Goods • Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.882		ASTM D792
Melt Mass-Flow Rate (MFR) (175°C/2.16 kg)	> 40	g/10 min	ASTM D1238
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress [2]			ASTM D412
Across Flow : 100% Strain	216	psi	
Flow : 100% Strain	261	psi	
Tensile Strength [2]			ASTM D412
Across Flow : Break	653	psi	
Flow : Break	618	psi	
Tensile Elongation [2]			ASTM D412
Across Flow : Break	770	%	
Flow : Break	650	%	
Tear Strength [2]			ASTM D624
Across Flow	106	lbf/in	
Flow	108	lbf/in	
Compression Set [3]			ASTM D395B
73°F, 22 hr	24	%	
158°F, 22 hr	44	%	

Revision Date: 10/13/2022

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Monprene® R2 CP-15155 NAT XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	60		
Shore A, 5 sec, Injection Molded	56		

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	311 to 374	°F
Middle Temperature	320 to 392	°F
Front Temperature	320 to 410	°F
Nozzle Temperature	320 to 410	°F
Processing (Melt) Temp	320 to 410	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Moderate-Fast	

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

[1] Typical properties: these are not to be construed as specifications.

[2] Die C, 20 in/min

[3] Type 1

Teknor Apex Company
Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan 22
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknoapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 10/13/2022

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector